Effect of hot and cold rolling on grain size and texture in FeSi strips with a Si-content larger than 2 wt%.

P. R. Calvillo¹, H. Hermann², J. Verstraete¹, J. Schneider^{1,2}, Y. Houbart¹

1. Metallurgy and Materials Science, Universiteit Gent, Gent-Zwijnaarde, Belgium; 2. Institut für Metallformung, Technische Universität Bergakademie Freiberg, Freiberg, Germany

The magnetic properties of electrical steel such as magnetization behaviour and specific magnetic losses are related to the microstructure and texture of the steel. The micro structural parameters having a strong influence on the magnetic properties are: grain size, inclusions, internal stresses and surface defects. They depend sensitively on the conditions during hot and cold rolling as well as on the final annealing treatment. Low values of the magnetic losses demand for large grain sizes and a large intensity of the cube texture is favourable for improved magnetization behaviour.

While the development of grain size and texture in conventional steels is already well understood, the knowledge for FeSi-alloys is far-off from complete. The interest in the case of FeSi-alloys is different from the case of conventional steels, where a high intensity of the {111} fibre and a small grain size is desired. In this paper we present and discuss some results of our recent studies on FeSi-alloys without phase transformation. Hot rolled samples of FeSi2.4 with a thickness of 2mm were fabricated using the four stand high speed hot rolling mill in Freiberg. The width of the hot rolled material is 80mm and the thickness is 2mm. The finishing temperature TF at hot rolling and the conditions for the following cooling down to 200°C have been varied in a wide range: 600 °C(TF) 1100°C; rapid cooling down to 400°C(TF) 750°C followed by slower cooling down to 200°C. The samples have been cold rolled to a final thickness of 0.50mm. Finally a thermal annealing comparable with the continuous annealing was used in a specially designed laboratory furnace. The maximum temperature was 950°C.

In addition to metallographic investigations, the EBSD-technique is used for micro structural and texture characterization. The resulting grain structure and the relevant magnetic texture components for non-grain oriented electrical steels: eta-, theta-, zeta- and Cube-fibres before and after cold rolling as well as after annealing were analyzed. According to the shape of the grains these were classified as equiaxed, pancake or bands in the deformed states. The homogeneity of the grain size and texture across the thickness, which is favoured to reach optimum magnetic properties, is also analyzed in the different states.

The resulting grain structure and texture was found to be rather inhomogeneous across the thickness for all realized and quite different hot rolling conditions. The re-crystallization takes place heterogeneously through the thickness. The intensity of the magnetically relevant textures, especially of cube and rotated cube texture in the hot strips can be increased by a slower cooling after hot rolling. Cold rolling does not destroy the obtained favourable magnetic texture components in the hot strips. Nevertheless, cold rolling results in a general, but moderate decrease of the relevant magnetic textures and in an increase of the alpha-fibre. Rapid cooling after finishing the hot rolling down to about 400°C gives bands in the material, only at the surface re-crystallization takes place. The intensities of the relevant magnetic texture components depend sensitively on the hot rolling conditions. Preliminary studies indicate that there is a large impact of the (Si,Al)-content and of the realized deformation in the different passes at hot rolling on the grain size and its distribution as well as on the resulting magnetic texture.

Finally present models for the development of texture after cold rolling and thermal annealing in steels are regarded with respect to their relevance for the FeSi alloys. It is pointed out that the under-

standing and modelling of the development of grain structure as well as of magnetic texture and their interaction needs further investigations.