HIGHLIGHTS AND BREAKTHROUGHS

Lessons from a lost technology: The secrets of Roman concrete

JAN ELSSEN^{1,*}, OZLEM CIZER² AND RUBEN SNELLINGS³

¹Department of Earth and Environmental Sciences, Katholieke Universiteit Leuven, B-3001 Leuven, Belgium

²Department of Civil Engineering, Katholieke Universiteit Leuven, B-3001 Leuven, Belgium

³Construction Materials Laboratory, Institute of Materials, EPFL, CH-1015 Lausanne, Switzerland

Abstract: “Roman concrete” was used as building material during Roman Imperial times for a great number of famous constructions with different functions. Well-known examples are aqueducts, for example the Pont du Gard in France and the Aqua Alexandrina in Rome, and numerous monuments such as the famous Coliseum and Pantheon in Rome. While visually less apparent today, ancient harbors also were an important part of constructions supporting the power of the Roman imperial system and were invaluable to control the Mediterranean Sea trade. The article “Unlocking the secrets of Al-tobermorite in Roman seawater concrete” by Jackson et al. (2013) describes the investigation of several extremely interesting samples drilled from 2000-year-old Roman maritime concretes in 11 harbors along the Mediterranean coast [the ROMACONS project 2002–2009 (Oleson et al. 2004)].

Keywords: Roman concrete, Pozzolana, Al-tobermorite, C-A-S-H

This article by Jackson et al. delivers an outstanding contribution because the described research integrates interdisciplinary findings from mineral physics, geochemistry, engineering, and archaeometry to investigate and explain reasons for the exceptional quality of these Roman constructions even after 2000-years exposure to an aggressive seawater environment. The article also gives novel results regarding the role of Al-tobermorite as the main cementitious binder in Roman concrete. Their results offer a source of new perspectives in future research on new binder types in the context of more sustainable and more durable concrete structures.

Ancient “Roman concretes” are complex composite cementitious materials with a hydraulic binder (“hydraulic” refers to the ability of the binder to harden under water) composed of a mixture of hydrated lime with volcanic material. Both the ancient Greeks and Romans knew that certain volcanic deposits when finely ground and mixed with lime and aggregates yielded hydraulic mortars and concrete with superior compressive strength

(Bleazard 1998). The Greek knowledge of the use of highly siliceous volcanic Santorini Earth (volcanic ash) goes back to 500–300 B.C., and around the third century B.C. the Romans discovered the effective use of “Pulvis Puteolanus” (meaning earthy material from the region of Puteoli and currently named pozzolana) near Mount Vesuvius. The use of these natural pozzolana and other supplementary cementitious materials [SCMs (Snellings et al. 2012)] will help in achieving improved durability of modern concretes and sustainable binder systems.

The advanced experimental methods utilized by the multi-disciplinary-authored team demonstrate that sharing knowledge and technical expertise from different scientific areas opens up fertile grounds for breakthrough research. In this case especially scanning transmission X-ray microscopy shed new light on the distribution of Al in the Al-tobermorite and calcium-aluminosilicate-hydrate (C-A-S-H) minerals, which form the main reaction products of Roman seawater concrete. The application of Al and Si X-ray absorption spectroscopy on dedicated instruments using synchrotron radiation at a nanometer spatial resolution is a first in the field and will certainly find more widespread application in construction materials science, applied mineralogy, and archaeometry. This analytical combination, with established characterization techniques in the field of historic mortars and concrete, such as solid state Al and Si NMR spectroscopy, and EMPA and SEM-EDX microanalysis, allowed the novel results to be compared and interpreted within the current state-of-the-art on cementitious binders.

The result is that the investigated ancient Roman seawater concrete is a highly complex and composite cementitious system with a remarkably heterogeneous structure. Its mix design needed no more than 10 wt% lime (quicklime, CaO) hydrated purposely in seawater after mixing with the key ingredient of alumina-rich volcanic ash. This notably unique combination formed the fundamental cementitious binding component, the glue, which, when mixed with pozzolanic coarse aggregates of zeolitic tuff, composed a unique concrete mixture that could set quickly under seawater, become extremely strong, and remain cohesive and intact in aggressive seawater for over 2000 years. The extraordinary durability of this massive seawater concrete is exceptional and must be related to the stability of the binder phase in an aggressive marine environment. Among the most interesting findings of the paper is the high content and differential distribution of Al in the C-A-S-H and Al-tobermorite binder phases. The chemical action of alkali cations, both from the volcanic ash and seawater, and the self-elevated moderate

* Present address: Department of Earth and Environmental Sciences, K.U.Leuven, Geo-instituut-Postbus 2410, Celestijnenlaan 200E, B-3001 Heverlee, Belgium. E-mail: jan.elsen@ees.kuleuven.be

temperatures (<85 °C) reached during the hydration of quicklime and formation of poorly crystalline C-A-S-H were identified to be critical to the formation of Al-tobermorite. Another eye-catching finding is related to the presence of sulfate, which is known to cause severe damages (i.e., delayed ettringite formation, expansion, and cracking) in today's concrete when it experiences internal temperatures above 70 °C, but surprisingly has no harm to this ancient seawater concrete. This particular performance is because sulfate ions are not bound in C-A-S-H but produce individual clusters of ettringite integrated soundly in the overall cementitious matrix. In this respect, the role of Al in stabilizing the phase assemblage, prohibiting dissolution, and deleterious expansive reactions is becoming clear (Chappex and Scrivener 2013), and connects to insights on mineral dissolution gained in the field of mineralogy and geochemistry (Schott et al. 2009). Furthermore, the work of Jackson et al. (2013) delivers an important fact that pozzolanic aggregates rich in silica, alumina, and alkalis undoubtedly contribute to the extended durability of this pozzolana-containing concrete without causing any damage from alkali-silica reaction, as opposed to today's common perception of concrete durability.

These findings clearly demonstrate successful ancient practice of Al- and alkali-rich binders, which are now appearing as sustainable and durable alternatives to Portland cement (Juenger et al. 2011). The well-recognized but overlooked superiority of the ancient seawater concrete containing natural pozzolana is obviously a tribute to the ingenuity of Roman scientists some 2000 years ago, as well as a proven model of extended durability and

sustainability from which we should learn to achieve improved durability of modern concrete structures and sustainable binder systems incorporating Al-tobermorite.

REFERENCES CITED

- Blezard, R.G. (1998) The history of calcareous cements. In P.C. Hewlett, Ed., *Lea's Chemistry of Cement and Concrete*, fourth ed. Butterworth Heinemann, London.
- Chappex, T., and Scrivener, K.L. (2013) The effect of aluminum in solution on the dissolution of amorphous silica and its relation to cementitious systems. *Journal of the American Ceramic Society*, 96, 592–597.
- Jackson, M.D., Chae, S.R., Mulcahy, S.R., Meral, C., Taylor, R., Li, P., Emwas, A.M., Moon, J., Yoon, S., Vola, G., Wenk, H.-R., and Monteiro, P.J.M. (2013) Unlocking the secrets of Al-tobermorite in Roman seawater concrete. *American Mineralogist*, 98, 1669–1687.
- Juenger, M.C.G., Winnefeld, F., Provis, J.L., and Ideker, J.H. (2011) Advances in alternative cementitious binders. *Cement and Concrete Research*, 41, 1232–1243.
- Oleson, J.P., Brandon, C., Cramer, S.M., Cucitore, R., Gotti, E., and Hohlfelder, R.L. (2004) The ROMACONS Project: A contribution to the historical and engineering analysis of hydraulic concrete in Roman maritime structures. *International Journal of Nautical Archaeology*, 33, 199–229.
- Schott, J., Pokrovsky, O.S., and Oelkers, E.H. (2009) The link between mineral dissolution/precipitation kinetics and solution chemistry. In E.H. Oelkers and J. Schott, Eds., *Thermodynamics and Kinetics of Water-Rock Interaction*, 70, 207–258. *Reviews in Mineralogy and Geochemistry*, Mineralogical Society of America, Chantilly, Virginia.
- Snellings, R., Mertens, G., and Elsen, J. (2012) Supplementary Cementitious Materials. In M.A.T.M. Broekmans and H. Pöllmann, Eds., *Applied Mineralogy of Cement & Concrete*, 74, 211–278. *Reviews in Mineralogy and Geochemistry*, Mineralogical Society of America, Chantilly, Virginia.

MANUSCRIPT RECEIVED JUNE 25, 2013

MANUSCRIPT ACCEPTED JULY 7, 2013

MANUSCRIPT HANDLED BY KEITH PUTIRKA

UNITED STATES POSTAL SERVICE® Statement of Ownership, Management, and Circulation		
(All Periodicals Publications Except Requester Publications)		
1. Publication Title American Mineralogist	2. Publication Number 0 0 2 0 0 7 6 0	3. Filing Date 08/28/2013
4. Issue Frequency eight issues a year	5. Number of Issues Published Annually 8	6. Annual Subscription Price \$100 (domestic)
7. Complete Mailing Address of Known Office of Publication (Not printer) (Street, city, county, state, and ZIP+4®) Mineralogical Society of America 3635 Concorde Pkwy Ste 500, Chantilly, VA 20151-1110		Contact Person J. Alex Speer Telephone (include area code) 703-652-9950
8. Complete Mailing Address of Headquarters or General Business Office of Publisher (Not printer) Mineralogical Society of America 3635 Concorde Pkwy Ste 500, Chantilly, VA 20151-1110		
9. Full Names and Complete Mailing Addresses of Publisher, Editor, and Managing Editor (Do not leave blank) Publisher (Name and complete mailing address) Mineralogical Society of America 3635 Concorde Pkwy Ste 500, Chantilly, VA 20151-1110 Editor (Name and complete mailing address) Keith Putirka and Ian Swanson, Mineralogical Society of America 3635 Concorde Pkwy Ste 500, Chantilly, VA 20151-1110 Managing Editor (Name and complete mailing address) Rachel A. Russell, Mineralogical Society of America 3635 Concorde Pkwy Ste 500, Chantilly, VA 20151-1110		
10. Owner (Do not leave blank. If the publication is owned by a corporation, give the name and address of the corporation immediately followed by the names and addresses of all stockholders owning or holding 1 percent or more of the total amount of stock. If not owned by a corporation, give the names and addresses of the individual owners. If owned by a partnership or other unincorporated firm, give its name and address as well as those of each individual owner. If the publication is published by a nonprofit organization, give its name and address.) Full Name Mineralogical Society of America Complete Mailing Address 3635 Concorde Pkwy Ste 500, Chantilly VA 20151-1110		
11. Known Bondholders, Mortgagees, and Other Security Holders Owning or Holding 1 Percent or More of Total Amount of Bonds, Mortgages, or Other Securities. If none, check box ☒ None Full Name Complete Mailing Address		
12. Tax Status (For completion by nonprofit organizations authorized to mail at nonprofit rates) (Check one) The purpose, function, and nonprofit status of this organization and the exempt status for federal income tax purposes: ☒ Has Not Changed During Preceding 12 Months ☐ Has Changed During Preceding 12 Months (Publisher must submit explanation of change with this statement)		

13. Publication Title American Mineralogist		14. Issue Date for Circulation Data Below 08/27/2013	
15. Extent and Nature of Circulation		Average No. Copies Each Issue During Preceding 12 Months	No. Copies of Single Issue Published Nearest to Filing Date
a. Total Number of Copies (Net press run)		1086	1090
b. Paid Circulation (By Mail and Outside the Mail)	(1) Mailed Outside-County Paid Subscriptions Stated on PS Form 3541 (Include paid distribution above nominal rate, advertiser's proof copies, and exchange copies)	467	428
	(2) Mailed In-County Paid Subscriptions Stated on PS Form 3541 (Include paid distribution above nominal rate, advertiser's proof copies, and exchange copies)	0	0
	(3) Paid Distribution Outside the Mails Including Sales Through Dealers and Carriers, Street Vendors, Counter Sales, and Other Paid Distribution Outside USPS®	423	406
	(4) Paid Distribution by Other Classes of Mail Through the USPS (e.g., First-Class Mail®)	0	0
c. Total Paid Distribution (Sum of 15b (1), (2), (3), and (4))		890	834
d. Free or Nominal Rate Distribution (By Mail and Outside the Mail)	(1) Free or Nominal Rate Outside-County Copies included on PS Form 3541	1	1
	(2) Free or Nominal Rate In-County Copies included on PS Form 3541	1	1
	(3) Free or Nominal Rate Copies Mailed at Other Classes Through the USPS (e.g., First-Class Mail)	0	0
	(4) Free or Nominal Rate Distribution Outside the Mail (Carriers or other means)	0	0
e. Total Free or Nominal Rate Distribution (Sum of 15d (1), (2), (3), and (4))		2	2
f. Total Distribution (Sum of 15c and 15e)		892	836
g. Copies not Distributed (See Instructions to Publishers #4 (page #3))		194	254
h. Total (Sum of 15f and g)		1086	1090
i. Percent Paid (15c divided by 15f times 100)		99.8	99.8
16. ☒ Total circulation includes electronic copies. Report circulation on PS Form 3526-X worksheet.			
17. Publication of Statement of Ownership ☒ If the publication is a general publication, publication of this statement is required. Will be printed in the Nov/Dec 2013 issue of this publication. ☐ Publication not required.			
18. Signature and Title of Editor, Publisher, Business Manager, or Owner J. Alex Speer MSA Executive Director			Date 08/27/2013

I certify that all information furnished on this form is true and complete. I understand that anyone who furnishes false or misleading information on this form or who omits material or information requested on the form may be subject to criminal sanctions (including fines and imprisonment) and/or civil sanctions (including civil penalties).