Citation	Lander Verstraete, Brandon E. Hirsch, John Greenwood and Steven De Feyter Confined Polydiacetylene Polymerization Reactions for Programmed Length Control Chemical Communications, 2014, 53, 4207-4210
Archived version	Author manuscript: the content is identical to the content of the published paper, but without the final typesetting by the publisher
Published version	insert link to the published version of your paper http://dx.doi.org/10.1039/c7cc00885f
Journal homepage	insert link to the journal homepage of your paper http://pubs.rsc.org/en/journals/journal/cc
Author contact	your email steven.defeyter@kuleuven.be your phone number + 32 (0)16 327921
IR	url in Lirias https://lirias.kuleuven.be/handle/123456789/578015

(article begins on next page)

Confined polydiacetylene polymerization reactions for programmed length control†

Q1 Q2

Cite this: DOI: 10.1039/c7cc00885f

Lander Verstraete, Brandon E. Hirsch,* John Greenwood‡ and Steven De Feyter*

 Received 2nd February 2017,
Accepted 7th March 2017

DOI: 10.1039/c7cc00885f

rsc.li/chemcomm

Polydiacetylene polymers of defined lengths are formed from self-assembled precursors inside nanocorrals created within grafted graphite substrates. A scanning tunneling microscope tip is used to nanoshave corrals at the liquid–solid interface allowing orientationally controlled supramolecular self-assembly of linear diacetylene molecules. Electrical pulses trigger topological one-dimensional polymerization reactions that are confined by the nanocorral template dimensions.

Morphology controlled polymer synthesis methods actively target size and shape homogeneity for applications ranging from separations to hardening materials.¹ Solution phase synthesis protocols such as dendritic growth, reversible addition-fragmentation chain transfer (RAFT), and other polymerization reactions have made significant progress in dimensionally controlled polymerization.² Nevertheless, controlling the topology and polydispersity remain active areas of polymer synthesis research. Alternatively, reactions that take advantage of supramolecular self-assembly events offer promising routes to control polymerization reactions by first spatially organizing the precursors units.³ In particular, structural control can be achieved in a rather facile preprogrammed fashion using interfacial, *i.e.*, air–liquid and liquid–solid self-assembly and synthesis methods.⁴ Work inside ultra-high vacuum (UHV) environments has also shown reactions involving coupling reactions and polymerizations.⁵ In this work, knowledge generated by the field of two-dimensional (2D) supramolecular self-assembly at liquid–solid interfaces is utilized to fabricate one-dimensional (1D) polymers of defined lengths inside corrals created on covalently modified highly oriented pyrolytic graphite (CM-HOPG) surfaces.

Polymerization of a self-assembled network of diacetylene monomers on surfaces has been well-studied over the past decade.⁶ Activation methods involving ultraviolet (UV) light irradiation or electrical pulses from a scanning tunneling microscope (STM) tip have been shown to initiate topochemical polymerization reactions to create conjugated polydiacetylene molecules.^{7–9} Using the latter method, nanometer scale precision over chain initiation has been presented.⁸ Additionally, property measurements of the conductivity through polydiacetylene thin films,¹⁰ or individual polymers of donor–acceptor–donor type¹¹ have been demonstrated. However, despite a high spatial selectivity over polymer initiation, the reaction termination step is poorly controlled, and thus the resultant length of the polydiacetylene polymer is often ill-defined.

Examples targeting confinement of surface reactions in UHV typically use vicinal¹² or periodically oxidized surfaces¹³ to localize precursors for polymerization and/or coupling reactions. In the specific case of polydiacetylene formation at the liquid–graphite interface, etch pits created by ion bombardment were employed as a means to constrain the reaction.¹⁴ Unfortunately, this method results in polydispersity due to a lack of control over pit formation. Here, the length of the polymer is controlled using nanocorrals precisely created in a CM-HOPG sample (Fig. 1). Covalent modification involves chemisorption of aryl radicals generated electrochemically from diazonium precursors.^{15,16} The covalently bound aryl molecules are removed in a systematic manner from the surface during a process called ‘nanoshaving’. In the nanoshaved corrals self-assembly can occur on freshly exposed graphite. This approach is reminiscent of the nanografting technique introduced by Liu *et al.*, in which an atomic force microscopy-based lithography technique is used to place foreign molecules inside a thiol matrix on gold.¹⁷ Similar work has also been done at aluminium oxide surfaces decorated with alkylphosphonates.¹⁸ In previous work, we demonstrated control over self-assembly inside corrals of different size, shape, and orientation.¹⁹ Here, the utility of these corrals is highlighted with the ability to predictably control the assembly and contain the dimension of subsequent reactions.

Department of Chemistry, Division of Molecular Imaging and Photonics, KU Leuven – University of Leuven, Celestijnenlaan 200F, B-3001 Leuven, Belgium

† Electronic supplementary information (ESI) available: Experimental details of the STM and grafting experiments; additional STM images. See DOI: 10.1039/c7cc00885f

‡ Present address: School of Physics & Astronomy, University of Nottingham, Nottingham, NG7 2RD, UK.

Fig. 1 (a) Schematic models of STM nanoshaving, PCDA self-assembly, and a tip induced polymerization reaction confined by nanocorrals formed inside CM-HOPG surfaces. (b) Chemical structure and schematic model of covalently bound 3,5-bis-*tert*-butylphenyl chemisorbed to a small sheet of graphene. (c) Chemical structure and schematic model of 10,12-pentacosadiynoic acid (PCDA) precursor. (d) Schematic model of the 1D-diacetylene polymerization reaction occurring inside the nanocorrals.

To establish diacetylene polymerization confinement and dimensionality control within the nanocorrals, 10,12-pentacosadiynoic acid (PCDA) (Fig. 1c) precursor molecules were chosen. A solution was prepared for liquid–solid self-assembly by saturating the compound in 1-phenyloctane solvent. Deposition of a small droplet ($\sim 5 \mu\text{L}$) on the freshly cleaved HOPG surface and subsequent STM imaging at the liquid–solid interface reveals linear lamellae structures (Fig. 2a and S1, ESI†). The self-assembled structure of PCDA on the HOPG surface optimizes hydrogen bonding and van der Waals interactions between the molecules (Fig. 2a and b). The unit cell for this structure is reported as $a = 6.6 \pm 0.1 \text{ nm}$, $b = 0.5 \pm 0.1 \text{ nm}$, $\alpha = 83.8 \pm 0.4^\circ$.¹⁹ Under the saturated conditions examined, domains of the PCDA assembly range from 100 nm^2 up to $10\,000 \text{ nm}^2$.

Polymerization of the self-assembled precursors was first examined on open terraces of freshly cleaved HOPG substrates to understand the nature of the reaction and to compare the reaction with previous studies.^{8,20} STM induced polymerization attempts were carried out using electrical pulses at -3.8 V for $10\text{--}110 \mu\text{s}$. Successful polymerization reactions are quite clear in the STM image as the newly formed polymers are imaged with a much brighter contrast than the self-assembled precursors (Fig. 2c). The brighter contrast has previously been attributed to the conjugated nature of the polymer and its topological change,^{7,8} that is evident in the schematic model inset presented in Fig. 2d. Similar to observations made by Aono and co-workers,⁸ domain boundaries limited the extent of the polymerization reaction (Fig. S2, ESI†). After pulsing, polymer propagation occasionally occurred in a divergent manner, however the two divergent polymers were always separated in space (Fig. S3, ESI†).

Fig. 2 (a) STM image of self-assembled PCDA precursors at the 1-phenyloctane–HOPG interface ($V_s = -0.8 \text{ V}$, $I_t = 100 \text{ pA}$). (b) Tentative model of the molecular organization of PCDA monomers on HOPG. (c) STM image of a polydiacetylene molecule created by applying an electrical pulse to a self-assembled network of PCDA ($V_s = -0.5 \text{ V}$, $I_t = 300 \text{ pA}$). (d) Tentative molecular model corresponding to the STM image in (c). Inset shows how the polydiacetylene backbone is raised from the surface.

In general, the polymers were found to be stable on the surface, however prolonged imaging frequently accompanied changes in the polymers. Repetitive STM imaging produced either partial or full desorption of the polymers (Fig. S3, ESI†). On occasion, broken polymers that indicate cutting events are also observed (Fig. S4, ESI†). Similar observations were also made in previous work by Kelly and co-workers for this molecular system.²¹

Covalent modification of the HOPG surface with a dense monolayer of chemisorbed species was accomplished using an electrochemical grafting procedure with an aqueous solution containing *in situ* generated diazonium cations. Using appropriate molecular design (3,5-bis-*tert*-butyldiazonium) and concentration (2.0 mM), a high density of chemisorbed molecules can be achieved on the surface using cyclic voltammetry (Fig. S5, ESI†). The resultant surface is decorated with newly formed sp^3 hybridized carbon–carbon bonds that covalently link the aryl compounds to the HOPG surface (Fig. 1b). Further experimental details are described in previous works.^{16,19,22} Nanocorrals are created within the dense monolayer of grafted aryls by raster scanning the desired area with the STM tip at high current ($I_t = 200 \text{ pA}$) and low sample bias ($V_s = -1 \text{ mV}$). These aggressive scanning conditions bring the tip in close proximity to the HOPG surface atoms allowing removal of the covalently bound aryl molecules. A full mechanistic understanding of this process is currently under more detailed investigation. Nevertheless, this tip-based removal of the aryls reverts the HOPG surface carbon atoms back to their original sp^2 hybridization.¹⁶

Fig. 3 (a–c) STM topography image sequence of (a) HOPG grafted with 3,5-TBD (2 mM) with a saturated solution of PCDA in 1-phenyloctane on top, (b) a nanocorral created in CM-HOPG with self-assembled PCDA inside; raster nanoshaving directions indicated by arrows, (c) a diacetylene polymer created after applying an electrical pulse of -3.8 V for $100\ \mu\text{s}$ (green arrow). (d and e) STM current images of PCDA molecules self-assembled with different orientations inside the “L” shaped corrals as a result of (d) nanoshaving orthogonal to or (e) nanoshaving parallel to a major graphite axis (red arrow). The orientational control produced from the nanoshaving yields polymers with well-controlled lengths that are governed by the dimensions of the corral and location of the electrical pulses (green arrows). All STM images are recorded with the following parameters: $V_s = -0.8$ V, $I_t = 60$ pA.

After the electrochemical grafting procedure, a droplet of PCDA in 1-phenyloctane is drop-casted on top of CM-HOPG surface. No self-assembly of PCDA on top or in between the grafted molecules is observed with such a dense monolayer of chemisorbed aryl molecules (Fig. 3a). However, when *in situ* nanoshaving is performed on the CM-HOPG, *i.e.* in the presence of the PCDA solution, the newly exposed HOPG surface becomes available for self-assembly of the PCDA molecules dissolved in the solution. Intelligent choice of the nanoshaving speed, direction, and shape allows control over the resultant PCDA self-assembled domain inside the nanocorral.¹⁹ When nanocorrals are created by rastering the STM tip across the surface with the slow nanoshaving direction orthogonal to a major axis of the HOPG surface, geometric constraints on the early stages of self-assembly kinetically favor the formation of PCDA lamellae along the slow nanoshaving direction (Fig. 3b). Importantly self-assembly is always observed within the time needed for nanoshaving and the subsequent imaging scan (~ 1 min). After nanocorral creation and PCDA self-assembly, a topochemical polymerization reaction was initiated with a local electrical pulse from the STM tip (-3.8 V for $100\ \mu\text{s}$) applied at the edge of the corral. In the following STM image a polymer is found to

propagate upward away from the location of the electrical pulse (Fig. 3c). The polymer extends to the opposite end of the nanocorral template, with its length being determined by the size of the host nanocorral and the location of the electrical pulse. From this initial experiment, it is clear that the corrals can be used to confine PCDA assembly and subsequent polymerization reactions.

Oriental control over the nanoshaving process as it relates to the graphite surface lattice directions allows one to easily select the nature of the precursor self-assembly inside the corral. Demonstration of the versatility afforded from these methods is shown by nanoshaving the same “L” shape in two different directions relative to the surface HOPG lattice. When nanoshaving is performed orthogonal to a major graphite axis, parallel PCDA lamellae are preferentially formed, and surface polymers of two distinct lengths can be created. Naturally, the two polymer lengths (37.3 nm and 11.9 nm) are correlated to the dimensions of the L-corrals and the position of electrical pulse (Fig. 3d). Alternatively, when the slow nanoshaving direction is parallel to a major axis of graphite, the PCDA lamellae are organized in a diagonal fashion within the corral (Fig. 3e). The diagonal arrangement is preferred as a result of

confinement effects during the nanoshaving process and favorable epitaxial interactions with the substrate. Upon electrical pulsing, the polymer lengths are less disperse (20.9 nm and 13.4 nm) than the polymers formed from the corral in Fig. 3d. In this case, the twofold utility of the corrals in controlling the polydispersity in the polymer chain length is well demonstrated; first by physically limiting the reaction and second by controlling the orientation of the precursor lamellae. Similarly, circular nanocorrals can be created for alternative polymer polydispersity inside the corrals (Fig. S6, ESI†). Different corral sizes and shapes, in combination with the self-assembly control afforded by the *in situ* nanoshaving process,¹⁹ provides multiple handles by which the reaction containers can be precisely dictated.

In conclusion, we have shown that conjugated polydiacetylene polymers with well-defined lengths can be fabricated by confining the liquid–solid molecular self-assembly of PCDA within nanocorrals created in CM-HOPG. This technique opens up a simple, versatile approach to control polymerization reactions by utilizing interfacial self-assembly methods inside surface nanocorrals. Coupling these nanoshaving methods with UV light irradiation experiments may foster greater throughput of the polymerization reactions.²³ Similarly, application of an array of scanning probes to simultaneously nanoshave the surface may allow scalability and further application in the fields of defined reaction synthesis methods.²⁴ This work emphasizes the utility of covalently modified surfaces and their top-down patterning by illuminating the unparalleled spatial and temporal control over self-assembly events and subsequent reactions.

This work has received funding from the Fund of Scientific Research–Flanders (FWO), KU Leuven Internal Funds, Belgian Federal Science Policy Office (IAP-7/05), and the European Research Council under the European Union's Seventh Framework Programme (FP7/2007-2013)/ERC Grant Agreement No. 340324. L. V. thanks the FWO for the fellowship received. B. H. acknowledges the Belgian American Educational Foundation and the FWO.

Notes and references

- 1 H.-G. Elias, *An Introduction to Polymer Science*, VCH, Weinheim, 1997.
- 2 A. M. Spokoyny, D. Kim, A. Sumrein and C. A. Mirkin, *Chem. Soc. Rev.*, 2009, **38**, 1218; A. Favier and M.-T. Charreyre, *Macromol. Rapid*

- Commun.*, 2006, **27**, 653; D. A. Tomalia, *Prog. Polym. Sci.*, 2005, **30**, 294.
- 3 L. Grill, M. Dyer, L. Lafferentz, M. Persson, M. V. Peters and S. Hecht, *Nat. Nanotechnol.*, 2007, **2**, 687; Y. Wang, A. S. Angelatos and F. Caruso, *Chem. Mater.*, 2008, **20**, 848; M. Bieri, S. Blankenburg, M. Kivala, C. A. Pignedoli, P. Ruffieux, K. Mullen and R. Fasel, *Chem. Commun.*, 2011, **47**, 10239.
- 4 L. Xu, X. Zhou, Y. Yu, W. Q. Tian, J. Ma and S. Lei, *ACS Nano*, 2013, **7**, 8066; H. Sahabudeen, H. Qi, B. A. Glatz, D. Tranca, R. Dong, Y. Hou, T. Zhang, C. Kuttner, T. Lehnert, G. Seifert, U. Kaiser, A. Fery, Z. Zheng and X. Feng, *Nat. Commun.*, 2016, **7**, 13461.
- 5 L. Dong, P. N. Liu and N. Lin, *Acc. Chem. Res.*, 2015, **48**, 2765; J. Shang, Y. F. Wang, M. Chen, J. X. Dai, X. Zhou, J. L. Kuttner, G. Hilt, X. Shao, J. M. Gottfried and K. Wu, *Nat. Chem.*, 2015, **7**, 389.
- 6 Y. Okawa, M. Akai-Kasaya, Y. Kuwahara, S. K. Mandal and M. Aono, *Nanoscale*, 2012, **4**, 3013.
- 7 A. Miura, S. De Feyter, M. M. S. Abdel-Mottaleb, A. Gesquiere, P. C. M. Grim, G. Moessner, M. Sieffert, M. Klapper, K. Mullen and F. C. De Schryver, *Langmuir*, 2003, **19**, 6474.
- 8 Y. Okawa and M. Aono, *J. Chem. Phys.*, 2001, **115**, 2317.
- 9 Y. Yang and M. B. Zimmt, *Langmuir*, 2015, **31**, 12408.
- 10 K. Takami, J. Mizuno, M. Akai-Kasaya, A. Saito, M. Aono and Y. Kuwahara, *J. Phys. Chem. B*, 2004, **108**, 16353.
- 11 C. Nacci, F. Ample, D. Bleger, S. Hecht, C. Joachim and L. Grill, *Nat. Commun.*, 2015, **6**, 7397.
- 12 B. Cirera, Y.-Q. Zhang, J. Björk, S. Klyatskaya, Z. Chen, M. Ruben, J. V. Barth and F. Klappenberger, *Nano Lett.*, 2014, **14**, 1891; A. Saywell, J. Schwarz, S. Hecht and L. Grill, *Angew. Chem., Int. Ed.*, 2012, **51**, 5096.
- 13 Q. T. Fan, J. Y. Dai, T. Wang, J. Kuttner, G. Hilt, J. M. Gottfried and J. F. Zhu, *ACS Nano*, 2016, **10**, 3747.
- 14 S. P. Sullivan, A. Schnieders, S. K. Mbugua and T. P. Beebe, *Langmuir*, 2005, **21**, 1322.
- 15 A. J. Downard, *Electroanalysis*, 2000, **12**, 1085; P. Allongue, M. Delamar, B. Desbat, O. Fagebaume, R. Hitmi, J. Pinson and J.-M. Savéant, *J. Am. Chem. Soc.*, 1997, **119**, 201; D. Belanger and J. Pinson, *Chem. Soc. Rev.*, 2011, **40**, 3995.
- 16 J. Greenwood, T. H. Phan, Y. Fujita, Z. Li, O. Ivasenko, W. Vanderlinden, H. Van Gorp, W. Frederickx, G. Lu, K. Tahara, Y. Tobe, H. Uji-i, S. F. L. Mertens and S. De Feyter, *ACS Nano*, 2015, **9**, 5520.
- 17 S. Xu and G. Y. Liu, *Langmuir*, 1997, **13**, 127; M. Liu, N. A. Amro and G. Y. Liu, *Annu. Rev. Phys. Chem.*, 2008, **59**, 367.
- 18 B. Torun, B. Ozkaya and G. Grundmeier, *Langmuir*, 2012, **28**, 6919.
- 19 L. Verstraete, J. Greenwood, B. E. Hirsch and S. De Feyter, *ACS Nano*, 2016, **10**, 10706.
- 20 S. K. Mandal, Y. Okawa, T. Hasegawa and M. Aono, *ACS Nano*, 2011, **5**, 2779.
- 21 R. Giridharagopal and K. F. Kelly, *J. Phys. Chem. C*, 2007, **111**, 6161.
- 22 A. M. Braganca, J. Greenwood, O. Ivasenko, H. Phan, K. Mullen and S. De Feyter, *Chem. Sci.*, 2016, **7**, 7028.
- 23 J. M. P. Alaboson, C. H. Sham, S. Kewalramani, J. D. Emery, J. E. Johns, A. Deshpande, T. Y. Chien, M. J. Bedzyk, J. W. Elam, M. J. Pellin and M. C. Hersam, *Nano Lett.*, 2013, **13**, 5763.
- 24 C. Liu, *Mater. Today*, 2008, **11**, 22.