MANUSCRIPT SUBMISSION

INTERNATIONAL JOURNAL OF GREENHOUSE GAS CONTROL

Environmental assessment of CO₂ mineralisation for sustainable construction materials

Authors:

Andrea DI MARIA

Sustainability Assessment of Material Life Cycle,
Katholieke Universiteit Leuven (KUL)

Ruben SNELLINGS

Sustainable Materials Unit,
Vlaamse Instelling voor Technologisch Onderzoek (VITO)

Luc ALAERTS

Sustainability Assessment of Material Life Cycle,
Katholieke Universiteit Leuven (KUL)

Mieke QUAGHEBEUR

Sustainable Materials Unit,
Vlaamse Instelling voor Technologisch Onderzoek (VITO)

Karel VAN ACKER

Katholieke Universiteit Leuven (KUL)
Center for Economics and Corporate Sustainability (CEDON),

Submitted: Friday 18th October, 2019

Environmental assessment of CO₂ mineralisation for sustainable construction materials*

Andrea DI MARIA¹, Ruben SNELLINGS², Luc ALAERTS¹, Mieke QUAGHEBEUR² and Karel VAN ACKER^{1,3}

¹Sustainability Assessment of Material Life Cycle, Katholieke Universiteit Leuven (KUL), Kasteelpark Arenberg 44 box 2450, BE-3001 Leuven, Belgium

²Sustainable Materials Unit, Vlaamse Instelling voor Technologisch Onderzoek (VITO), Boeretang 200, 2400 Mol, Belgium

³Center for Economics and Corporate Sustainability (CEDON), KU Leuven, Warmoesberg 26, BE-1000 Brussels, Belgium

Submitted: October 18th, 2019

Abstract

Mineral carbonation is a carbon utilisation technology in which an alkaline material reacts with carbon dioxide forming stable carbonates that can have different further uses, for instance as construction material. The alkaline material can be a residue from industrial activities (e.g. metallurgic slags) while CO₂ can be recovered from industrial flue gasses. Mineral carbonation presents several potential environmental advantages: (i) industrial residues valorisation, (ii) CO₂ sequestration and (iii) substitution of conventional concrete based on Portland cement (PC).

However, both the carbonation and the CO₂ recovery processes require energy. To understand the trade-off between the environmental benefits and drawbacks of CO₂ recovery and mineral carbonation, this study presents a life cycle assessment (LCA) of carbonated construction blocks from mineral carbonation of stainless steel slags. The carbonated blocks are compared to traditional PC-based concrete blocks with similar properties.

The results of the LCA analysis show that the carbonated blocks present lower environmental impacts in most of the analysed impact categories. The key finding is that the carbonated blocks present a negative carbon footprint. Nonetheless, the energy required represents the main environmental hotspot. An increase in the energy efficiency of the mineral carbonation process and a CO₂ valorisation network are among the suggestions to further lower the environmental impacts of carbonated blocks production.

Finally, the LCA results can promote the development of policy recommendations to support the implementation of mineral carbonation technology. Further research should enable the use of mineral carbonation on a broader range and large volume of alkaline residues.

*Draft manuscript. Please do not cite without the authors' permission.

Keywords— Mineral Carbonation, Stainless steel slag, Life cycle assessment, CO₂ capture and utilisation

1 Introduction

The IPCC special report on the “impacts of global warming of 1.5 °C” suggests that to limit global warming within 1.5 °C, the global net anthropogenic CO₂ emission needs to decline 45% from 2010 level by 2030 (IPCC, 2018). Carbon capture and utilisation (CCU) techniques have gained attention worldwide, because they can turn CO₂ emissions into a valuable resource for new products, such as fuels and chemicals (Balucan et al., 2013; Giannoulakis et al., 2014). Therefore, CCU technologies can contribute to climate change mitigation and, at the same time, increase the economic profitability of carbon capture processes (Cuéllar-Franca and Azapagic, 2015; Styring et al., 2011). However, the current markets for these products alone cannot provide a sufficient demand, compared to the amount of CO₂ emitted globally (Cuéllar-Franca and Azapagic, 2015). Another possibility to utilise the captured CO₂ is mineral carbonation, a process which produces carbonated materials as a long-term storage for CO₂ (Di Maria et al., 2018; Kelly et al., 2011; Mo et al., 2017; Salman et al., 2013, 2014). Mineral carbonation involves the capture of CO₂ in a mineral form by its reaction with alkaline materials, to form solid carbonate products that can be used, for instance, in construction activities (Santos et al., 2013). The alkaline materials for mineral carbonation can be (i) naturally occurring rocks and minerals, or (ii) residues from industrial processes, such as steel or cement manufacturing. (Hampel, 1968). The use of alkaline industrial residues for mineral carbonation is especially promising since their estimated global carbonation potential may increase to 3.3 GtCO₂/y⁻¹ in 2100, which could represent between the 5% and 12% of the 2100 global CO₂ emissions (Renforth, 2019). Additionally, alkaline industrial residues can be carbonated in situ in the same plant where they are produced, avoiding waste transports to external treatment plants

(IPCC, 2005).

Following the framework indicated by the IPCC special report on Carbon dioxide and Capture Storage (IPCC, 2005), mineral carbonation using alkaline industrial residues can be schematized as illustrated in figure 1. The alkaline industrial residues used for mineral carbonation are residues containing calcium and magnesium-rich oxides and silicates.

Although mineral carbonation is seen today as one of the most promising technology offering a cost-effective climate change mitigation, several barriers are still hindering its deployment at an industrial scale, such as technical feasibility, economic viability, and the lack of legislative framework for carbon recovery (Olajire, 2013; Salman et al., 2016; Santos et al., 2013). Additionally, a sustainable environmental profile is another fundamental prerequisite for a successful large-scale deployment of new technologies. Mineral carbonation is an energy-intensive process, since the kinetics of the reaction must be accelerated by a combination of increased temperature and higher CO₂ concentration. Thanks to the enhanced reaction conditions, the carbonation rate can be 40 times higher than the rate of natural carbonation (Sanjuán et al., 2003). However, the increased reaction kinetics are at the expense of additional energy needs, which may partially offset the environmental benefits.

In this regard, several studies have been published on the environmental performances of mineral carbonation, but only a few have focused specifically on the mineral carbonation using industrial alkaline residues (some of these studies are listed in table 1 and will be discussed later). All the previous LCA studies are based on data from literature or lab-scale developments. However, when upscaling of a process at an industrial level, the process parameters will be tailored to the utilised alkaline raw material, optimising its resources consumption (energy, water, materials) compared to a lab-scale development (Shibasaki et al., 2006). Therefore, data from real industrial applications are massively needed. Following this need, the current study presents a life-cycle-assessment (LCA)

of a mineral carbonation process performed at a real industrial demonstrator, built and operated in Belgium by the company “Orbix”. The process uses stainless steel slag (SSS) as alkaline media for the process. SSS has been chosen thanks to its high carbonation potential (Baciacchi et al., 2010; Capobianco et al., 2014; Salman et al., 2014; Santos et al., 2013) and to its high availability, with 0.5 Mt processed each year in Belgium (Quaghebeur et al., 2015).

LCA is a methodology that allows to estimate the environmental impacts attributable to a product or a process along its life cycle (Pennington et al., 2004; Rebitzer et al., 2004). The previous LCA studies listed in table 1 have identified the energy used for mineral carbonation as one the factor causing the main environmental impact of the process. Another major impact is caused by the CO₂ recovery, which is an energy intensive process that captures CO₂ from industrial waste gas (Di Maria et al., 2018; Khoo et al., 2011b; Salman et al., 2016). Although mineral carbonation does not require a 100% purity of the CO₂ gas stream, a high purity increases the kinetics of the reaction and, consequently, it lowers the time needed to complete the process. Additionally, waste gas from industrial processes can contain impurities such as SO_x or Cl₂ that will compete with the CO₂ in binding the free lime or the calcium silicates, lowering the carbonation efficiency. Therefore, although possible, studies have demonstrated that working with lower grade CO₂ can compromise the economics of the carbonation process.

All analysed LCA studies assumed that CO₂ is recovered through chemical absorption by methylethanolamine (MEA), which is today the most common technique for CO₂ capturing and recovering from industrial flue gas. However, for CO₂ recovery there is no a “one-size-fits-all” technology”, and several techniques are today available to ensure compatibility with the specific industry producing the CO₂-containing flue gas (Cuéllar-Franca and Azapagic, 2015). Each of these techniques presents technical and environmental advantages and disadvantages that should be considered when evaluating the most appropriate CO₂ source for mineral carbonation. For this

reason, the current study compares the environmental performances of three different techniques for CO₂ recovery: (i) cryogenic process; (ii) membrane separation; (iii) chemical absorption through MEA. Although many other possibilities for CO₂ recovery are available, the above-mentioned techniques are increasingly drawing the interest of the Belgian industry. The LCA for the considered CO₂ recovery process is based on data gathered from previous literature. The inclusion of the CO₂ recovery process into the system boundaries provides a more complete and realistic evaluation of an eventual mineral carbonation facility integrated in an industrial CO₂ valorisation network. Finally, the LCA results of the carbonated blocks production are compared to the LCA results of the traditional PC-based concrete available in the market, to find the trade-off between environmental impacts caused by the CO₂ capturing and the carbonation process, and the benefits of the CO₂ storage and the substitution of raw material-based product in the market.

Table 1: Overview of literature LCA studies on mineral carbonation using alkaline industrial residues

Study	Goal	FU	Alkaline Material	(CO ₂ capture method and data source)	(Data source for mineral carbonation)	Results
(Bodéan et al., 2014)	To assess the feasibility and the environmental performances of ex-situ mineral carbonation to mining waste	Production of 1 MWh of electricity with a coal power plant	Mafic/ultramafic mining waste, pyrometallurgical slag	MEA	Experimental results at lab scale	The LCA results varied greatly depending on the carbonation process studied. A commercial application for the carbonation product can reduce the global environmental impact
(Chang et al., 2011)	To evaluate the environmental performances of carbonation for several steel slags	1 kg of carbonated slags	Steel slags	Non considered	Experimental results at lab scale	Energy consumption represents the highest impact during mineral carbonation, in particular due to the heating process
(Di Maria et al., 2018)	LCA of carbonation compared to traditional concrete	Compressive strength provided by 1 m ² of the compared materials	Industrial by-product (Stainless steel slag)	MEA (ecoinvent)	Experimental results at lab scale	Carbonated blocks show a lower impact compared to traditional concrete. CO ₂ production and electricity consumption in carbonation are the environmental hotspot of carbonation process.
(Mattila et al., 2014)	Comparative LCA of two processes for precipitated-calcium-carbonate production: Carbonation of lime vs carbonation of steel slag	Production of 1 kg of final product	Steel slags	CO ₂ taken directly from flue gas stream	Literature sources and process simulations	Carbonation of steel slags in precipitated calcium carbonate production has several advantages, possible post-treatment steps of the products and residues should be included.
(Kirchofer et al., 2013)	Comparison of the carbonation performances of different alkaline materials from industrial residues	Storage CO ₂ potential of different alkaline materials	Cement kiln dust, fly ash, steel slag	Not specified	Literature	The CO ₂ mitigation potential of carbonation depends on the carbonation potential of each alkaline material and its local availability.

Figure 1: The mineral carbonation concept using alkaline industrial residue: CO₂-containing flue gas is generated by industrial processes, as for instance steel or power plants. The CO₂ from the flue gas is then recovered through a CO₂-recovery process, and then utilised in the mineral carbonation plant, where alkaline industrial residues are carbonised to produce carbonated blocks that can be used by the construction industry.

2 Materials and methods

2.1 Mineral carbonation

When CO₂ reacts with the metal oxides (MO) contained in the alkaline material, it forms the corresponding carbonate, following the chemical reaction:

Figure 2: Schematic drawing of the Carbstone® production process on a lab scale (Quaghebeur et al., 2015)

where M is the divalent metal, such as calcium or magnesium. The mineral carbonation process analysed in this study refers to an industrial demonstrator producing carbonated blocks using SSS as alkaline material. The carbonated blocks are called Carbstone®, a patented technology developed to produce high strength building materials by treating slags with CO_2 at elevated pressure and temperature, without the addition of binders (Quaghebeur et al., 2015). Figure 2 shows a schematic overview of the Carbstone® production process. It consists of three main steps: (i) pre-treatment of the slag, (ii) shaping of the building blocks and (iii) CO_2 curing of the building blocks in an autoclave.

Two variants of the carbonation process have been developed at the industrial demonstrator: a low-pressure process for the production of common building blocks (compressive strength up to 50 MPa) and a high-pressure process for the production of high-strength materials (compressive strength > 50 MPa). In this study, the low-pressure process was selected, as this process may be the first one commercialised in Belgium. The low-pressure process is based on a recipe in which the raw material mix consists of a mixture of 50% dried fine-grained stainless steel slags and 50% fine sand.

The SSS used in the process is produced by the company Orbix, located in Genk, Belgium. The chemical composition of the SSS is reported in table 2 (further details on the characterisation of the slag (including micro-elements such as Cr, Mo, Ba and others) can be found in Quaghebeur (2015).

Table 2: Average composition of the SSS used in the carbonation process (Quaghebeur et al., 2015)

Main elements	WT%
CaO	45 $\pm$ 0.5
MgO	9.3 $\pm$ 2.3
Fe ₂ O ₃	1.5 $\pm$ 0.9
MnO	1.4 $\pm$ 0.09
SiO ₂	31 $\pm$ 5.3
Al ₂ O ₃	3.0 $\pm$ 0.1

2.2 Life cycle assessment

According to the ISO 14040:2006 (ISO, 2006), a LCA is carried out in four different phases: definition of goal and scope, life cycle inventory (LCI), life cycle impact assessment (LCIA), results interpretation and conclusions.

2.2.1 Goal and scope and functional unit

The goal of the LCA presented in this study is to provide an environmental analysis of carbonated blocks produced through carbonation of SSS. Three different scenarios are compared for the production of the carbonated blocks. Each scenario uses a different CO₂ recovery process as a source of CO₂ for the mineral carbonation. The carbonated blocks are further compared to the PC-based concrete blocks presenting similar properties. The results of the environmental analysis will help to identify the environmental benefits and weaknesses of the production of SSS-based carbonated

blocks. In addition, the comparison between carbonated SSS-based blocks and PC-based concrete will help to understand the potential environmental effect of the mineral carbonation technology in the construction sector when replacing traditional PC-based concrete based products.

The functional unit is a fundamental parameter in LCA, as it defines the reference to which all calculations are performed during the study. It also identifies the function that serves as base for comparison of two products. The analysed blocks are used for walls construction. In this application the key technical function is the compressive strength. Therefore, the functional unit of the study refers to the capacity of the carbonated blocks and the PC-based concrete blocks to provide a specific compressive strength. The compressive strength can be defined as the capacity of a materials to withstand a load without fractures, and it is measured in MPa (N/mm^2). As a reference for the proposed functional unit, the LCA compares the production of 1 m^2 of carbonated blocks with 1 m^2 of PC-based concrete blocks, with both materials able to provide an equal compressive strength of 40MPa. The compared surfaces are made of 50 blocks, each measuring 20 cm (length), 10 cm (width) and 4 cm (thickness), for a total volume of 800 cm^3 (0.008 m^3).

2.2.2 System boundaries and life cycle inventory inventory

Carbonated blocks The flow diagram for the production of the carbonated blocks is shown in Figure 3, that also indicates the boundaries of the analysed system for the LCA study. The SSS (0-60 mm) is used as alkaline material. No transport of the SSS to the mineral carbonation plant is considered. This assumption will not significantly affect the results since, as demonstrated by various authors, the effect of transports of alkaline residues is rather small on the overall LCI of the carbonation process (Khoo et al., 2011b, 2011a; Slotte, 2017).

According to the data collected at the industrial demonstrator, the carbonated blocks present a compressive strength of 43 MPa, 2.5% total inorganic carbon and a density of 2300 kg / m^3 . To

161 produce the required volume defined by the functional unit (0.008 m³, with a weight of 92 kg) 44.2
162 kg of SSS are carbonated. The different steps for the carbonated blocks production and the data
163 inventory are summarised in table 3 and figure 4.

164 Before entering the carbonation process, the SSS undergoes a pre-treatment for metal recovery. In
165 the pre-treatment, some metals are recuperated from the SSS using a wet mechanical treatment. The
166 metals are reused as a raw material for the production of stainless steel. However, data on metals
167 recovery were not disclosed, and therefore not included in the scope of this analysis. Although the
168 lack of data on metals recovery can be considered as a limitation of the study, the available data on
169 energy consumption and CO₂ requirements from an industrial demonstrator can provide relevant
170 indications on the overall environmental impacts of the mineral carbonation process.

171 After the pre-treatment, the SSS enters the carbonation plant. First, the fine, wet slag is dried before
172 entering the mixing process. The sand used is the same kind of sand used as fine aggregate in PC
173 concrete . The mixture SSS-water-sand is then shaped via compacting (pressing). The shaped mix,
174 which has the desired dimensions but only minimal strength, is then placed in a curing reactor where
175 it is put into contact with 8.5 kg CO₂ at elevated pressure (5 bar), in a CO₂ (> 90%) atmosphere. No
176 CO₂ is released in the atmosphere during the curing. The stream of CO₂ used in the curing reactor
177 is considered to be generated by three different CO₂-recovery processes: cryogenic separation
178 (scenario 1), membrane separation (scenario 2) and chemical absorption via MEA (scenario 3). A
179 more detailed description of the inventory for the three processes is reported in the next section
180 of this paper. The reaction of CO₂ with the Ca and Mg bearing minerals in the SSS forms the
181 carbonates that yield the required compressive strength. The carbonated blocks resulting from the
182 curing process are immediately ready to be commercialised.

Figure 3: Analysed system and boundaries of the LCA for the carbonated blocks

CO₂ recovery As mentioned above, the study presents three scenarios, where CO₂ is obtained from three different sources: flue gases from steel plants or waste incineration plants (CO₂ concentrations of 10 to 20% (Mikunda et al., 2015), fermenters producing biogas (25-55% CO₂ (Zhang et al., 2013)), and ammonia production waste gas (the initial concentration of CO₂ is not declared by the CO₂ producers from ammonia waste streams). The three gas streams undergo a CO₂ recovery process that concentrates the CO₂ for carbonation. Each process could potentially recover CO₂ from different gas streams, as for instance chemical absorption can be applied both to steel plant flue gas and ammonia production waste gas. Hence, for the purpose of simplicity, the three considered scenarios refer to the classification presented by Cuéllar-Franca and Azapagic (2012), which report the most commonly used gas stream for each CO₂ recovery processes:

- Scenario 1: cryogenic process (in the case of steel flue gas)
- Scenario 2: membrane separation (in the case of biogas)
- Scenario 3: chemical absorption through monoethanolamine (MEA) (in the case of ammonia production waste gas)

It is assumed that the three CO₂ recovery processes produce a pure CO₂ gas stream. Although a purity of 100% of the CO₂ gas stream is not required by the carbonation process, a lower CO₂ concentration generally prologues the carbonation process.

S1- Cryogenic separation of CO₂ from flue gas S1 focuses on the recovery of CO₂ from steel production and waste incineration via cryogenic separation. Cryogenic separation is a relatively novel technology that removes CO₂ from flue gas in a liquid or solid form. The CO₂ obtained from the cryogenic separation can be readily reused for the carbonation process (Tuinier et al., 2010). In a cryogenic separation system, the CO₂ is separated from other gasses by condensing it

at extremely low temperature. The amount of CO₂ recovered ranges between 90-95% of all CO₂ initially contained in the flue gas (Khoo and Tan, 2006). Therefore, the main advantages of the cryogenic CO₂ separation are that no chemical absorbents are required and that the process can be operated at atmospheric pressure (Clodic et al., 2005). On the other hand, the high energy demand required to keep the process at low temperature may affect the environmental performance of the cryogenic process. As reported by Khoo and Tan (2006), cryogenic CO₂ separation requires 630 kWh per ton of CO₂ recovered as liquid form.

S2- Membrane separation of CO₂ from Biogas In S2, a membrane separation process is used to separate the CO₂ from the biogas produced by an anaerobic digester for organic waste. Membrane separation is a physical process that allows CO₂ to pass through a membrane while excluding all other gasses. Polymeric gas separation membranes are the most common membranes used for CO₂ recovery, with an energy demand around 75 kWh per ton of CO₂ recovered, which is determined mostly by the pressure ratio needed across the membrane, and a removal rate around 82-88% of CO₂ from the biogas (Khoo and Tan, 2006). Additionally, as shown in figure 3 for scenario 2, the membrane separation of biogas produces a double output: the CO₂ stream on one side, and purified biogas (mostly concentrated CH₄) on the other side. Therefore, when accounting for the environmental impact of CO₂ recovery through membrane separation, the impact must be allocated between the two products (CO₂ and purified biogas). According to the ISO 14044 (2006), allocation in LCA is defined as the partitioning of the inputs/outputs of a multifunctional process between the product under study and the other products of the process. The use of market price as allocation criteria is often found in practice. The allocation based on prices is commonly used because of its simplicity and its ability to summarise complex attributes of the different products produced during a multifunctional process (Ardente and Cellura, 2012). For the current study, the

environmental impacts arising from the membrane separation process are allocated between CO₂ and purified biogas according to their market prices. According to Mikunda et al. (2015), the price of purified biogas in 2015 is 168 USD/t, while the market price of liquid CO₂ is 115 USD/t. Therefore, 41% of the impacts from the membrane separation process are assigned to the CO₂ production, while the 59% are assigned to the purified biogas production.

S3- Chemical absorption of CO₂ via MEA S3 analyses the CO₂ recovery through chemical absorption during ammonia production. Chemical absorption by solvents is the most widely used process for CO₂ removal, while MEA is the most commonly used solvent in this process (Cuéllar-Franca and Azapagic, 2015). The MEA is completely regenerated during the process, but high heat consumption is required for solvent regeneration. Data for the CO₂ chemical absorption considered in this study refer to the dataset described by Althaus et al. (2007), which also represents the reference process for CO₂ chemical absorption in the Ecoinvent 3.3 database. This dataset represents the extraction and purification of CO₂ from an ammonia production flue gas. The energy demand is estimated to be 400 kWh per ton of CO₂ recovered.

PC-based concrete The concrete mix design represents the ratio between cement, sand and coarse aggregates in concrete, and it plays a critical role in defining concrete performances such as durability, compressive strength and workability. The concrete mix design for a required compressive strength can be calculated using the BRMCA methods, developed by the British Ready Mixed Concrete Association (Newman and Choo, 2003). Based on the BRMCA calculation for the required compressive strength of 40 MPa, the PC-based concrete has a density of 2360 kg/m³, and the design mix is 360 kg/m³ of cement CEM I, 620 kg/m³ of sand, 1200 kg/m³ of coarse aggregates and 180 kg/m³ of water. All data for the inventory of PC-based concrete production are also summarised in

251 table 3 and in figure 4.

Table 3: Life cycle inventory for the carbonated blocks and the PC-based concrete blocks

Functional unit	
Volume	0.08 m ³
Carbonated blocks	
Density	2300 kg/m ³
weight (as reference of the functional unit)	92 kg
<u>Drying</u>	
SSS (kg)	44.2
Thermal energy	5.8 kWh
<u>Mixing</u>	
Electricity	2.5 kWh
Water	9.8 kg
Sand	44.2 kg
<u>Curing</u>	
Electricity	0.2 kWh
CO ₂	8.5 kg
Water (released)	7.9 kg
CO₂ recovery	
<i>S1-Cryogenic</i>	
Electricity	5.3 (kWh)
<i>S2-Membrane</i>	
Electricity	0.3 kWh
<i>S3- Chemical absorption</i>	
Electricity	3.4 (kWh)
PC-based concrete	
Density	2360 kg/m ³
weight (as reference of the functional unit)	94.4 kg
<u>PC-based concrete production</u>	
CEM I	14.4 kg
Gravel	48 kg
Sand	24.8 kg
Water	7.2 kg

Carbonated blocks **PC-based concrete**

Figure 4: Life cycle inventory for the carbonated blocks and the PC-based concrete. The inconsistency in the mass balance of carbonated blocks production (total input: 106.7 kg , total output: 99.9 kg) derives from the challenge in accounting the exact amount of water that is released during curing. Part of this water is created by the carbonation of hydroxides and hydrates in the SSS and it can be recycled

2.2.3 Life Cycle impact assessment

The life cycle impact assessment (LCIA) uses specific characterisation models to translate the inventory data into environmental impact categories. Characterisation models usually refer to two main approaches: the “problem-oriented”, or midpoint, and the “damage-oriented”, or endpoint. The midpoint analysis assesses the contribution of each material/energy flow to several different environmental categories, while the endpoint analysis identifies environmental issues potentially

damaging the three main aspects of the natural environment, namely human health, ecosystem and natural resources.

As previously discussed by many authors (see for instance Benetto et al. (2004) or Kägi et al. (2015)), the midpoint analysis provides results that are reliable, since they are based on scientifically sound methods. However, midpoint results may not answer questions such as “is product A environmentally better than product B?”, as some midpoint categories may show different tendencies than others. The decision-makers, which are considered among the final users of the LCA results, may consequently base their decision on an arbitrary weighting method, dependent on their subjective interests and experiences. In order to avoid decisions based on subjective considerations, the midpoint analysis can be aggregated to the endpoint level. The endpoint method proposes a weighting procedure that aggregates the results from the midpoint categories to endpoint damages. Although the results from the endpoint analysis are easier to be interpreted and compared, they contain additional uncertainty due to the aggregation and weighting process. Therefore, the combination of midpoint and endpoint results can assist in better interpretation and transparency: the midpoints allows to detect the highest contributing processes and to find possible room for improvements; the endpoint provides a general picture of the environmental costs and benefits for each scenario, making the results easy to be compared with results from other scenarios (Di Maria et al., 2018). For the reasons discussed above, the current study presents the LCIA results in both midpoint and endpoint.

For the midpoint analysis, the International Reference Life Cycle Data System (ILCD) v.1.09 framework is used. The ILCD framework, developed by the European Commission- Joint Research Centre (EC-JRC), selects the recommended methods for each midpoint impact category starting from a pre-selection of existing methods. For instance, for the category climate change, the recommended calculation method is the IPCC model with 100-year time-horizon, while for human toxicity the ILCD recommends the USEtox model 2008. A more detailed explanation of all the

ILCD recommended methods for midpoint analysis can be found in JRC (2011).

On the other hand, no recommendations are currently provided within the ILCD framework for endpoint analysis, because of the unavailability of sufficiently mature models for most of the endpoint categories. Therefore, the endpoint analysis performed in the current study refers to the another widely accepted environmental assessment methodology, called Recipe, which includes three endpoint environmental damages: (i) human health damage, (ii) loss of species in ecosystems, and (iii) resources depletion (Goedkoop et al., 2012).

3 Results

The results of the midpoint analysis are shown in figure 5. The comparison between the three scenarios for carbonated blocks and the PC-based concrete (columns from left to right: S1, S2, S3, PC-based concrete) is shown for each midpoint category. Since midpoint categories are expressed in different units, the results are normalised to the scenario having the highest impact (expressed as 100% in the graph). The traditional PC-based concrete has the highest impacts in nine out of the sixteen analysed midpoint categories (acidification, climate change biogenic and non-biogenic, ecotoxicity freshwater, eutrophication freshwater, human toxicity cancer and non-cancer effect, land use, resource depletion minerals). For instance, considering the category climate change including biogenic carbon (carbon that is already within the carbon cycle), the carbonated blocks present an emission reduction of 68% for S1, 77% for S2 and 71% for S3, compared to the PC-based concrete emissions. On top of that, the negative part of the graph in both climate change categories (biogenic and non-biogenic) represents the amount of CO₂ uptaken by the carbonated blocks during the carbonation process (8.5 kg). The results show that the final CO₂-equivalent balance (the difference between the CO₂-equivalent emitted minus the CO₂-equivalent uptake) is negative for all carbonated

blocks scenarios (-1.09 kg and -1.01 kg for S1; -1.96 kg and -1.90 kg for S2; -1.36 kg and -1.28 kg for S3). Therefore, mineral carbonation is a negative-carbon-footprint technology, since the amount of CO₂ uptake and stored during the process is higher than the amount of CO₂ emitted, considering the whole life cycle. The carbonated blocks also present significant impact reductions in the categories eutrophication freshwater (-64% for S1, -77% for S2, -69% for S3), human toxicity non cancer effect (-51% for S1, -73% for S2, -60% for S3) and resource depletion of minerals (-60% for S1, -72% for S2, -65% for S3). On the other hand, the carbonated blocks technology presents higher impacts compared to PC-based concrete in the categories eutrophication marine and terrestrial, ionising radiation, ozone depletion, particulate matter, photochemical ozone formation and resource depletion water. Looking at the single process contribution, the highest quota in almost all categories is given by the production and use of diesel in the drying process (equal for all carbonated blocks scenarios). The only difference between the three carbonated blocks scenarios is the electricity consumption to recover the CO₂ from the different sources. Since cryogenic CO₂ recovery is the technology requiring the highest amount of electricity, S1 is the scenario with the highest impacts. The electricity for CO₂ recovery has a most relevant contribution (>50% on the total impact of the carbonated blocks) for S1 in the categories ionising radiation (63%) and resource depletion water (55%). Finally, as expected, for all analysed categories, cement production causes the highest contribution to the final impact of PC-based concrete.

Figure 5: Midpoint results (AE: Acidification;GWP100: Climate change midpoint, excl biogenic carbon; GWP100bio: Climate change midpoint, incl biogenic carbon; CTUe: Ecotoxicity freshwater;P: Eutrophication freshwater; N: Eutrophication marine; AEutr: Eutrophication terrestrial; CTUhcan: Human toxicity, cancer effects; CTUh: Human toxicity, non-cancer effects; U235: Ionizing radiation, human health; LU: Land use; ODP: Ozone depletion; PM2.5: Particulate matter/Respiratory inorganics; POF: Photochemical ozone formation, human health; RDW: Resource depletion water; RDF: Resource depletion, mineral, fossils and renewables)

The midpoint analysis provides a detailed description of the cause-effect relationship between emissions and their direct effect on the environment. However, the results in figure 5 do not help to conclude which is the material with the lowest environmental impact, as the analysed cases show different trends in different categories. Therefore, an aggregation to the endpoint can help to identify which of the analysed materials presents the best environmental profile. Figure 6 shows the results of the endpoint analysis. PC-based concrete shows the highest impacts in the damages human health and ecosystems, while S1 has the highest impact on the damage resources. The scenario S2 has the lowest contribution for all three damages, while S3 has a higher impact compared to PC concrete only in the damage resources. Looking at the contributions of every single process, the endpoint results confirm the outcomes of the midpoint analysis. For the damages human health and ecosystems, the avoided impacts from the CO₂ uptake are higher than the impacts caused by the production of the carbonated blocks, for all three scenarios. At the same time, cement production contributes to 95% of the total impact of PC-based concrete. For the damage resources, the electricity and diesel consumption during the carbonated blocks production process have the highest contribution for all carbonation scenarios.

Figure 6: Endpoint results

3.1 Interpretation and limitations

The LCIA results discussed above highlight the environmental advantages and disadvantages of the production of the carbonated blocks compared to the production of traditional PC-based concrete. The midpoint analysis showed how carbonation technology presents a significant reduction in some categories such as climate change, where the impact is reduced by 70% compare to the PC-based concrete. Moreover, the results show that the amount of CO₂ uptake and stored within the carbonated blocks is higher than the CO₂ emitted during the whole mineral carbonation process. This negative-carbon balance is also confirmed by the endpoint analysis, where human health and

ecosystem present a negative impact for all carbonation scenarios. Among the three considered carbonation scenarios, the S2 always presents the lowest impacts, due to the lower energy required by the membrane CO₂ recovery process.

On the other hand, in some other midpoint categories and the endpoint damage resources, all the carbonation scenarios present higher impacts compared to the traditional PC-based concrete. Looking at the single processes, the highest contribution for the carbonated blocks production is given by the fossil fuels used during the drying process. Therefore, a reduction of the moisture content in the wet slag, or an increased optimisation of the drying process could sensibly reduce the impacts of the carbonated blocks. This may lead to further improve the environmental profile of the carbonated blocks, especially for those categories where the carbonated blocks present a higher impact compared to PC-based concrete. The electricity consumption for CO₂ recovery significantly affects the final impact of the carbonated blocks (>50%), especially in S1, for ionising radiation and water depletion in the midpoint, and resources in the endpoint.

It must also be noticed that carbonation of SSS (and in general any technology based on the recovery of metallurgic slag to produce new construction materials) is a constrained technology, meaning that the production capacity (or supply) is inelastic, as it cannot be adjusted to meet an increase in demand for the product. Due to the difference between the price of the stainless steel and the price of the SSS, the production is driven by the demand for stainless steel rather than the demand for SSS. Consequently, the metallurgic process will focus on the properties of stainless steel, rather than on the quality and volumes of the SSS. Therefore, variable compositions of the SSS may affect the technical and environmental performance of the carbonated blocks.

Finally, it is also worth to highlight the limitations of the presented LCA results. A first limitation is represented by the assumptions made to solve the allocation issue. First, an allocation problem arises when deciding what share of the environmental burdens of the stainless steel production

generating the SSS should be allocated to the carbonated blocks. Following the Waste Framework Directive 2008/98/EC and the recommendations put forth in the ISO 14041, an allocation coefficient should indeed be applied only if the waste can be considered as a by-product, while no allocation is advised if the waste is considered as an unintended residue. So far, SSS does not have the status of a by-product, because of the uncertainty on its further use as secondary resources.

Consequently, SSS is today legally considered as waste material. Therefore, for the LCA presented in this paper, the allocation procedure has been avoided, and no impacts are attributed to the SSS. However, in the future, the carbonation technology is expected to develop, and further applications of an allocation coefficient for SSS may be needed, although, given the price ratio between stainless steel and slag, the effect may be limited.

Another limitation of the LCA study is represented by the intrinsic limitation of LCA when it comes to industrial decision-making and evaluation of industrial symbiosis applications. As clarified by Marvuglia et al., (2013) and Vázquez-Rowe et al. (2014), the traditional LCA approach (known as attributional approach) provides a sound environmental analysis and understanding of the main environmental impacts within the concerned production system. On the other hand, it omits the analysis of potential indirect effects engendered in the markets. Therefore, attributional LCA results provide an excellent environmental analysis at a product level, which enables a reliable comparison between alternative products. However, an expansion of the analysed system may be required to draw significant conclusions on the environmental consequences of product substitution.

4 Conclusions and perspectives

Aiming at the reduction of carbon dioxide (CO₂) emissions, carbon capture utilisation (CCU) technologies are raising the attention of the industries and the scientific community. Among the

CCU technologies, mineral carbonation acts by chemically binding CO₂ in alkaline materials to produce a stable carbonated block that can be used by the construction industry. The CO₂ can be recovered from flue gases derived from carbon-intensive industrial processes, while the alkaline material can be a solid residue from other industries. Therefore, mineral carbonation can have several potential environmental benefits: (i) the valorisation of residues from other industries, (ii) the recovery of CO₂ from industrial flue gases, (iii) substitution of traditional PC-based construction blocks with negative or low-carbon products.

On the other hand, the energy required by the carbonation and the CO₂ recovery processes may offset the beneficial effects. To understand the overall environmental performance of mineral carbonation, this study presents a life cycle assessment (LCA) of carbonated blocks made from stainless steel slag (SSS). The data for the carbonation process is collected from a real industrial demonstrator situated in Belgium. The study analyses three different scenarios, based on literature data for three techniques for CO₂ recovery: (i) cryogenic process; (ii) membrane separation; (iii) chemical absorption through MEA. Finally, the study compares the environmental performance of the carbonated blocks with the ones of traditional Portland cement (PC) based concrete with equivalent technical performance.

The results of the midpoint analysis show that the carbonated blocks have lower environmental impacts in nine out of sixteen impact categories, compared to PC-based concrete. For instance, all three carbonation scenarios present a significant reduction in global warming potential. A key finding is that the results show that the quantity of CO₂ uptake by the carbonation process is higher than the quantity of CO₂ emitted by the process. Therefore, the mineral carbonation process to produce carbonated blocks from stainless steel slag residue can be considered as a potentially negative carbon-footprint technology. The results of the endpoint analysis confirm that for the damages to human health and ecosystems, the carbonated blocks have a lower impact compared to the traditional PC-based concrete, and an overall negative impact.

On the other hand, although the industrial demonstrator showed a significant increase in the energy efficiency of the process compared to previous LCA studies based on lab-scale data, the energy consumption represents the main environmental hotspot. As a consequence of the energy requirements, the carbonation process has higher impacts in seven midpoint categories and the endpoint damage resources. Therefore, the future industrial development of mineral carbonation should further increase the energy efficiency of the process and find alternative sources for electricity and heat requirements, such as recovery of waste heat of the exothermal carbonation process. Another environmental hotspot highlighted by the LCA study is the electricity consumption for the CO₂ recovery process. This result confirms the outcomes of previous LCA studies. The comparison between the CO₂ recovery technologies showed that membrane separation is the technology with the lowest environmental impacts based on available data.

Nonetheless, when integrated into the carbonation process, all analysed technologies present environmental advantages. In this context, to support the introduction of the technology and development of industrial synergies, the development of CO₂ valorisation networks should be facilitated. Legislative frameworks and infrastructure development should be supported by the public sector, to enable CO₂ stream sharing between neighbour industries. Also a symbiosis network/platform for material streams exchange can serve as a base to the further development of a CO₂ valorisation network.

The construction sector is considered a critical sector for sustainability, and LCA represents an opportunity in this context. For instance, the implementation of green certificates based on LCA reports can be an essential asset to increase green public procurements for mineral carbonation. Green public procurement is a powerful tool to drive the whole sector towards sustainable production, as the public sector plays a vital and pioneering role in the market. Moreover, mineral carbonation represents an economic opportunity for the construction sector, since it can replace conventional

PC-based concrete, which requires the extraction of primary raw materials, and it produces a significant amount of CO₂ emissions which, in Europe, can incur significant financial costs in the EU emission trading system . At the same time, quarrying activities are under increasing environmental and societal pressure or are subject to spatial constraints.

On the other hand, mineral carbonation of SSS is a resource-constrained technology, depending on the production of stainless steel. Therefore the quality and the quantity of SSS available for carbonation is dependent on the demands for the stainless steel. Consequently, future development of SSS carbonation technology will not likely change the amount of SSS available. In Belgium, for instance, a SSS production of 500 kt/y has been calculated, while recent data estimates a cement PC production in Belgium of 6500 kt/y. It is clear that the carbonated blocks from SSS can represent only a small share of the total construction materials market in Belgium. Therefore, ongoing research is currently undertaken to use other alkaline residues, such as concrete demolition waste, incineration and biomass ashes. This can strongly expand the volumes of secondary raw materials available for the mineral carbonation process.

5 Acknowledgements

All authors are very grateful for financial support received from the Flemish administration via the Steunpunt Circulaire Economie (Policy Research Centre Circular Economy). This publication contains the opinions of the authors, not that of the Flemish administration. The Flemish administration will not carry any liability with respect to the use that can be made of the produced data or conclusions.

6 Declaration of conflict of interest

ORBIX and VITO collaborated in the development of the Carbstone technology and have acquired joint intellectual property. KU Leuven took part in the study as an independent party, therefore KU Leuven declares no conflict of interest.

7 References

- Althaus, H.J., Hischer, R., Osses, M., Primas, A., Jungbluth, N., Chudacoff, M., 2007. Life Cycle Inventories of Chemicals. Final report ecoinvent data v.2.0 No. 8, Ecoinvent report n.8. EMPA, Swiss Centre for Life Cycle Inventories, Dübendorf.
- Ardente, F., Cellura, M., 2012. Economic Allocation in Life Cycle Assessment. *J. Ind. Ecol.* 16, 387–398. <https://doi.org/10.1111/j.1530-9290.2011.00434.x>
- Bacocchi, R., Costa, G., Bartolomeo, E. Di, Poletti, A., Pomi, R., 2010. Carbonation of stainless steel slag as a process for CO₂ storage and slag valorization. *Waste and Biomass Valorization* 1, 467–477. <https://doi.org/10.1007/s12649-010-9047-1>
- Balucan, R.D., Dlugogorski, B.Z., Kennedy, E.M., Belova, I. V., Murch, G.E., 2013. Energy cost of heat activating serpentinites for CO₂ storage by mineralisation. *Int. J. Greenh. Gas Control* 17, 225–239. <https://doi.org/10.1016/J.IJGGC.2013.05.004>
- Benetto, E., Rousseaux, P., Blondin, J., 2004. Life cycle assessment of coal by-products based electric power production scenarios. *Fuel* 83, 957–970. [https://doi.org/10.1016/S0016-2361\(03\)00258-8](https://doi.org/10.1016/S0016-2361(03)00258-8)
- Bodéan, F., Bourgeois, F., Petiot, C., Augé, T., Bonfils, B., Julcour-Lebigue, C., Guyot, F., Boukary, A., Tremosa, J., Lassin, A., Gaucher, E.C., Chiquet, P., 2014. Ex situ mineral carbonation for CO₂ mitigation: Evaluation of mining waste resources, aqueous carbonation processability and life cycle assessment (Carmex project). *Miner. Eng.* 59, 52–63. <https://doi.org/10.1016/J.MINENG.2014.01.011>
- Capobianco, O., Costa, G., Thuy, L., Magliocco, E., Hartog, N., Bacocchi, R., 2014. Carbonation of stainless steel slag in the context of in situ Brownfield remediation. *Miner. Eng.* 59, 91–100. <https://doi.org/10.1016/J.MINENG.2013.11.005>
- Chang, E.E., Pan, S.-Y., Chen, Y.-H., Chu, H.-W., Wang, C.-F., Chiang, P.-C., 2011. CO₂ sequestration by carbonation of steelmaking slags in an autoclave reactor. *J. Hazard. Mater.* 195, 107–114. <https://doi.org/http://dx.doi.org/10.1016/j.jhazmat.2011.08.006>

- Clodic, D., Bill, A., Casier, F., Hitti, R. El, Younes, M., 2005. CO₂ capture by anti-sublimation Thermo-economic process evaluation, in: 4 Th Annual Conference on Carbon Capture Sequestration. Alexandria (VA), USA.
- Cuéllar-Franca, R.M., Azapagic, A., 2015. Carbon capture, storage and utilisation technologies: A critical analysis and comparison of their life cycle environmental impacts. *J. CO₂ Util.* 9, 82–102. <https://doi.org/10.1016/J.JCOU.2014.12.001>
- Cuéllar-Franca, R.M., Azapagic, A., 2012. Environmental impacts of the UK residential sector: Life cycle assessment of houses. *Build. Environ.* 54, 86–99. <https://doi.org/http://dx.doi.org/10.1016/j.buildenv.2012.02.005>
- Di Maria, A. Di, Salman, M., Dubois, M., Acker, K. Van, 2018. Life cycle assessment to evaluate the environmental performance of new construction material from stainless steel slag. *Int. J. Life Cycle Assess.* 1–19. <https://doi.org/10.1007/s11367-018-1440-1>
- Giannoulakis, S., Volkart, K., Bauer, C., 2014. Life cycle and cost assessment of mineral carbonation for carbon capture and storage in European power generation. *Int. J. Greenh. Gas Control* 21, 140–157. <https://doi.org/10.1016/j.ijggc.2013.12.002>
- Goedkoop, M., Heijungs, R., Huijbregts, M.A.J., De Schryver, A.M., Struijs, J., van Zelm, J.R., 2012. ReCiPe 2008 - A life cycle impact assessment method which comprises harmonised category indicators at the midpoint and the endpoint level.
- Hampel, C.A., 1968. *The Encyclopedia of the Chemical Elements*. Reinhold Book Corporation.
- IPCC, 2018. *Global Warming of 1.5°C. An IPCC Special Report on the impacts of global warming of 1.5°C above pre-industrial levels and related global greenhouse gas emission pathways, in the context of strengthening the global response to the threat of climate change.*
- IPCC, 2005. *Special Report on CO₂ Capture and Storage*, Intergovernmental Panel on Climate Change. <https://doi.org/10.1002/anie.201000431>
- ISO, 2006. *ISO 14040. Environmental management - life cycle assessment - principles and frameworks*. Int. Organ. Stand.
- JRC, 2011. *ILCD Handbook: Recommendations for Life Cycle Assessment in the European Context*. Publication Office of the European Union. <https://doi.org/10.278/33030>
- Kägi, T., Dinkel, F., Frischknecht, R., Humbert, S., Lindberg, J., De Mester, S., Ponsioen, T., Sala, S., Urs, , Schenker, W., 2015. CONFERENCE SESSION REPORT: SETAC EUROPE 25TH ANNUAL MEETING Session "Midpoint, endpoint or single score for decision-making";-SETAC Europe 25th Annual Meeting. <https://doi.org/10.1007/s11367-015-0998-0>
- Kelly, K.E., Silcox, G.D., Sarofim, A.F., Pershing, D.W., 2011. An evaluation of ex situ, industrial-scale, aqueous CO₂ mineralization. *Int. J. Greenh. Gas Control* 5, 1587–1595. <https://doi.org/10.1016/J.IJGGC.2011.09.005>
- Khoo, H.H., Bu, J., Wong, R.L., Kuan, S.Y., Sharratt, P.N., 2011a. Carbon capture and utilization: Preliminary life cycle CO₂, energy, and cost results of potential mineral carbonation. *Energy Procedia* 4, 2494–2501. <https://doi.org/10.1016/J.EGYPRO.2011.02.145>

- Khoo, H.H., Sharratt, P.N., Bu, J., Yeo, T.Y., Borgna, A., Highfield, J.G., Bjorklof, T.G., Zevenhoven, R., 2011b. Carbon Capture and Mineralization in Singapore: Preliminary Environmental Impacts and Costs via LCA. *Ind. Eng. Chem. Res.* 50, 11350–11357. <https://doi.org/10.1021/ie200592h>
- Khoo, H.H., Tan, R.B.H., 2006. Life cycle investigation of CO₂ recovery and sequestration. *Environ. Sci. Technol.* 40, 4016–4024. <https://doi.org/10.1021/es051882a>
- Kirchofer, A., Brandt, A., Krevor, S., Prigiobbe, V., Becker, A., Wilcox, J., 2013. Assessing the Potential of Mineral Carbonation with Industrial Alkalinity Sources in the U.S. *Energy Procedia* 37, 5858–5869. <https://doi.org/10.1016/J.EGYPRO.2013.06.510>
- Marvuglia, A., Benetto, E., Rege, S., Jury, C., 2013. Modelling approaches for consequential life-cycle assessment (C-LCA) of bioenergy: Critical review and proposed framework for biogas production. *Renew. Sustain. Energy Rev.* 25, 768–781. <https://doi.org/10.1016/j.rser.2013.04.031>
- Mattila, H.P., Hudd, H., Zevenhoven, R., 2014. Cradle-to-gate life cycle assessment of precipitated calcium carbonate production from steel converter slag. *J. Clean. Prod.* 84, 611–618. <https://doi.org/10.1016/j.jclepro.2014.05.064>
- Mikunda, T., Neele, F., Wilschut, F., Hanegraaf, M., 2015. A secure and affordable CO₂ supply for the Dutch greenhouse sector.
- Mo, L., Zhang, F., Deng, M., Jin, F., Al-Tabbaa, A., Wang, A., 2017. Accelerated carbonation and performance of concrete made with steel slag as binding materials and aggregates. *Cem. Concr. Compos.* 83, 138–145. <https://doi.org/10.1016/J.CEMCONCOMP.2017.07.018>
- Newman, J. (John B., Choo, B.S., 2003. *Advanced concrete technology*. [v. 1], Constituent materials. Butterworth-Heinemann.
- Olajire, A.A., 2013. A review of mineral carbonation technology in sequestration of CO₂. *J. Pet. Sci. Eng.* 109, 364–392. <https://doi.org/10.1016/J.PETROL.2013.03.013>
- Pennington, D.W., Potting, J., Finnveden, G., Lindeijer, E., Jolliet, O., Rydberg, T., Rebitzer, G., 2004. Life cycle assessment Part 2: Current impact assessment practice. *Environ. Int.* 30, 721–739. <https://doi.org/10.1016/j.envint.2003.12.009>
- Quaghebeur, M., Nielsen, P., Horckmans, L., Van Mechelen, D., 2015. Accelerated Carbonation of Steel Slag Compacts: Development of High-Strength Construction Materials. *Front. Energy Res.* 3, 52. <https://doi.org/10.3389/fenrg.2015.00052>
- Rebitzer, G., Ekvall, T., Frischknecht, R., Hunkeler, D., Norris, G., Rydberg, T., Schmidt, W.-P., Suh, S., Weidema, B.P., Pennington, D.W., 2004. Life cycle assessment: Part 1: Framework, goal and scope definition, inventory analysis, and applications. *Environ. Int.* 30, 701–720. <https://doi.org/10.1016/j.envint.2003.11.005>
- Renforth, P., 2019. The negative emission potential of alkaline materials. *Nat. Commun.* 10, 1401. <https://doi.org/10.1038/s41467-019-09475-5>
- Salman, M., Cizer, Ö., Pontikes, Y., Santos, R.M., Snellings, R., Vandewalle, L., Blanpain, B., Van Balen, K., 2014. Effect of accelerated carbonation on AOD stainless steel slag for its valorisation as a CO₂-sequestering construction material. *Chem. Eng. J.* 246, 39–52. <https://doi.org/10.1016/j.cej.2014.02.051>

- Salman, M., Dubois, M., Maria, A. Di, Van Acker, K., Van Balen, K., 2016. Construction Materials from Stainless Steel Slags: Technical Aspects, Environmental Benefits, and Economic Opportunities. *J. Ind. Ecol.* 20, 854–866. <https://doi.org/10.1111/jiec.12314>
- Salman, Ö., Cizer, Y., Pontikes, L., Vandewalle, B., Blanpain, K., Van Balen, 2013. Carbonation potential of continuous casting stainless steel slag. *KU Leuven*, pp. 319–329.
- Sanjuán, M., Andrade, C., Cheyrez, M., 2003. Concrete carbonation test in natural and accelerated conditions Study of durability for concrete in Marine Atmosphere View project Radioactivity in Spain View project. *Adv. Cem. Res.* 15. <https://doi.org/10.1680/adcr.2003.15.4.171>
- Santos, R.M., Bouwel, J. Van, Vandeveld, E., Mertens, G., Elsen, J., Gerven, T. Van, 2013. Accelerated mineral carbonation of stainless steel slags for CO₂ storage and waste valorization: Effect of process parameters on geochemical properties. *Int. J. Greenh. Gas Control* 17, 32–45. <https://doi.org/http://dx.doi.org/10.1016/j.ijggc.2013.04.004>
- Shibasaki, M., Warburg, W., Eyerer, P., 2006. Upscaling effect and Life Cycle Assessment.
- Slotte, M., 2017. Two Process Case Studies on Energy Efficiency, Life Cycle Assessment and Process Scale-up. Abo Akademi University.
- Styring, P., Jansen, D., de Coninck, H., Armstrong, K., 2011. Carbon Capture and Utilisation in the green economy.
- Tuinier, M.J., van Sint Annaland, M., Kramer, G.J., Kuipers, J.A.M., 2010. Cryogenic CO₂ capture using dynamically operated packed beds. *Chem. Eng. Sci.* 65, 114–119. <https://doi.org/10.1016/J.CES.2009.01.055>
- Vázquez-Rowe, I., Marvuglia, A., Rege, S., Benetto, E., 2014. Applying consequential LCA to support energy policy: Land use change effects of bioenergy production. *Sci. Total Environ.* 472, 78–89. <https://doi.org/10.1016/j.scitotenv.2013.10.097>
- Zhang, Y., Sunarso, J., Liu, S., Wang, R., 2013. Current status and development of membranes for CO₂/CH₄ separation: A review. *Int. J. Greenh. Gas Control* 12, 84–107. <https://doi.org/10.1016/J.IJGGC.2012.10.009>
- setspace

8 Figures

Figure 1: The mineral carbonation concept using alkaline industrial residue: CO₂-containing flue gas is generated by industrial processes, as for instance steel or power plants. The CO₂ from the flue gas is then recovered through a CO₂-recovery process, and then utilised in the mineral carbonation plant, where alkaline industrial residues are carbonised to produce carbonated blocks that can be used by the construction industry.

Figure 2: Schematic drawing of the Carbstone® production process on a lab scale (Quaghebeur et al., 2015)

Figure 3: Analysed system and boundaries of the LCA for the carbonated blocks

Carbonated blocks **PC-based concrete**

Figure 4: Life cycle inventory for the carbonated blocks and the PC-based concrete. The inconsistency in the mass balance of carbonated blocks production (total input: 106.7 kg , total output: 99.9 kg) derives from the challenge in accounting the exact amount of water that is released during curing. Part of this water is created by the carbonation of hydroxides and hydrates in the SSS and it can be recycled

Figure 5: Midpoint results (AE: Acidification;GWP100: Climate change midpoint, excl biogenic carbon; GWP100bio: Climate change midpoint, incl biogenic carbon; CTUe: Ecotoxicity freshwater;P: Eutrophication freshwater; N: Eutrophication marine; AEutr: Eutrophication terrestrial; CTUhcan: Human toxicity, cancer effects; CTUh: Human toxicity, non-cancer effects; U235: Ionizing radiation, human health; LU: Land use; ODP: Ozone depletion; PM2.5: Particulate matter/Respiratory inorganics; POF: Photochemical ozone formation, human health; RDW: Resource depletion water; RDF: Resource depletion, mineral, fossils and renewables)

Figure 6: Endpoint results

9 Tables

Table 1: Overview of literature LCA studies on mineral carbonation using alkaline industrial residues

Study	Goal	FU	Alkaline Material	(CO ₂ capture method and data source)	(Data source for mineral carbonation)	Results
(Bodéan et al., 2014)	To assess the feasibility and the environmental performances of ex-situ mineral carbonation to mining waste	Production of 1 MWh of electricity with a coal power plant	Mafic/ultramafic mining waste, pyrometallurgical slag	MEA	Experimental results at lab scale	The LCA results varied greatly depending on the carbonation process studied. A commercial application for the carbonation product can reduce the global environmental impact
(Chang et al., 2011)	To evaluate the environmental performances of carbonation for several steel slags	1 kg of carbonated slags	Steel slags	Non considered	Experimental results at lab scale	Energy consumption represents the highest impact during mineral carbonation, in particular due to the heating process
(Di Maria et al., 2018)	LCA of carbonation compared to traditional concrete	Compressive strength provided by 1 m ² of the compared materials	Industrial by-product (Stainless steel slag)	MEA (ecoinvent)	Experimental results at lab scale	Carbonated blocks show a lower impact compared to traditional concrete. CO ₂ production and electricity consumption in carbonation are the environmental hotspot of carbonation process.
(Mattila et al., 2014)	Comparative LCA of two processes for precipitated-calcium-carbonate production: Carbonation of lime vs carbonation of steel slag	Production of 1 kg of final product	Steel slags	CO ₂ taken directly from flue gas stream	Literature sources and process simulations	Carbonation of steel slags in precipitated calcium carbonate production has several advantages, possible post-treatment steps of the products and residues should be included.
(Kirchofer et al., 2013)	Comparison of the carbonation performances of different alkaline materials from industrial residues	Storage CO ₂ potential of different alkaline materials	Cement kiln dust, fly ash, steel slag	Not specified	Literature	The CO ₂ mitigation potential of carbonation depends on the carbonation potential of each alkaline material and its local availability.

Table 2: Average composition of the SSS used in the carbonation process (Quaghebeur et al., 2015)

Main elements	WT%
CaO	45 ± 0.5
MgO	9.3 ± 2.3
Fe ₂ O ₃	1.5 ± 0.9
MnO	1.4 ± 0.09
SiO ₂	31 ± 5.3
Al ₂ O ₃	3.0 ± 0.1

Table 3: Life cycle inventory for the carbonated blocks and the PC-based concrete blocks

Functional unit	
Volume	0.08 m ³
Carbonated blocks	
Density	2300 kg/m ³
weight (as reference of the functional unit)	92 kg
<u>Drying</u>	
SSS (kg)	44.2
Thermal energy	5.8 kWh
<u>Mixing</u>	
Electricity	2.5 kWh
Water	9.8 kg
Sand	44.2 kg
<u>Curing</u>	
Electricity	0.2 kWh
CO ₂	8.5 kg
Water (released)	7.9 kg
CO₂ recovery	
<i>S1-Cryogenic</i>	
Electricity	5.3 (kWh)
<i>S2-Membrane</i>	
Electricity	0.3 kWh
<i>S3- Chemical absorption</i>	
Electricity	3.4 (kWh)
PC-based concrete	
Density	2360 kg/m ³
weight (as reference of the functional unit)	94.4 kg
<u>PC-based concrete production</u>	
CEM I	14.4 kg
Gravel	48 kg
Sand	24.8 kg
Water	7.2 kg