Efficient, high-CRI white LEDs by combining traditional phosphors with cadmium-free InP/ZnSe red quantum dots

BEGA KARADZA,¹ HANNES VAN AVERMAET,², LEILA MINGABUDINOVA,², ZEGER HENS,² AND YOURI MEURET^{1,*}

¹KU Leuven, Department of Electrical Engineering (ESAT), Light&Lighting Laboratory, Gebroeders De Smetstraat 1, 9000 Gent, Belgium

²Physics and Chemistry of Nanostructures and Center for Nano and Biophotonics, Krijgslaan 281-S3, 9000 Gent, Belgium

*Corresponding author: youri.meuret@kuleuven.be

Abstract: Quantum dots offer an interesting alternative for traditional phosphors in on-chip LED configurations. Earlier studies showed that the spectral efficiency of white LEDs with high CRI values could be considerably improved by replacing red-emitting nitride phosphors with narrow-band QDs. However, the red QDs in these studies were cadmium-based, which is a restricted element in the EU under the RoHS directive. The use of InP-based QDs, the most promising Cd-free alternative, is often presented as an inferior solution because of the broader linewidth of these QDs. However, while narrow emission lines are the key to display applications that require a large color gamut, the spectral efficiency penalty of this broader emission is limited for lighting applications. Here, we report efficient, high-CRI white LEDs with an on-chip color convertor coating based on red InP/ZnSe QDs and traditional green/yellow powder phosphors. Using InP/ZnSe QDs with a quantum yield of nearly 80% and a full width at half maximum of 45 nm, we demonstrate high spectral efficiency for white LEDs with very high CRI values. One of the best experimental results in terms of both luminous efficacy and color rendering performance is a white LED with an efficacy of 132 lm/W, and color rendering indices of $R_a \approx 90$, $R9 \approx 50$ for CCT ≈ 4000 K. These experimental results are critically compared with theoretical benchmark values for white LEDs with on-chip down-conversion from both phosphors and red Cd-based QDs. The various loss mechanisms in the investigated white LEDs are quantified with an accurate simulation model, and the main impediments to an even higher efficacy are identified as the blue LED wall-plug efficiency and light recycling in the LED package.

© 2021 Optical Society of America under the terms of the OSA Open Access Publishing Agreement

1. Introduction

The performance of phosphor-converted white LED technology rises steadily towards its physical limits. Luminous efficacy has almost doubled in the last ten years, but the achieved values are still considerably lower than the theoretically calculated maxima [1]. Further improvements are possible by increasing blue-chip and package efficiency, as well as the spectral efficiency by developing fluorescent materials with optimal optical characteristics and a high photoluminescence quantum yield (PLQY).

Efficiency, however, is not the only property that determines the quality of a white LED. The ability to reproduce colors faithfully in comparison with an ideal or natural light source is a second, very important characteristic. The CIE (International Commission on Illumination) has defined an internationally agreed method to quantify the ability of a light source to render color [2]. Their most widely used metric (CIE R_a) is based on the shift of the chromaticity coordinates of predefined test color samples (TCS) when illuminated by the light source is a black

body emitter when the light source has a correlated color temperature (CCT) below 5000 K. A maximum value of 100 is obtained when there are no color differences for each TCS. A total of 14 TCS are specified in the CIE 13.3-1995 report. While R_a is an average quantity that covers the first eight samples, R9 is an individual rendering index for the highly saturated red TCS2, [3]. This R9 value is often added to the Ra value in order to have a more complete description of the color rendering performance. While other color rendering metrics have appeared in recent years, the CIE R_a metric is still the industry standard [3]. The California Energy Commission (CEC) standard recommends a CRI (the CIE R_a value) of at least 90 and an R9 value of at least 50 [4], requirements we refer to as Ra 90, R9 50. This recommendation matches with the general customer preferences for color fidelity [5,6]. Although the Ra 90, R9 50 requirements were enacted back in 2013, their adoption by industry takes time due to the significant efficiency penalty that relates to the transition from Ra 80 to Ra 90 [6]. This penalty is mainly caused by the broad emission of the red nitride phosphors that are typically used in white LEDs. These phosphors have an emission band that extends deep into the red region of the visible spectrum, where the reduced sensitivity of the human eye leads to a strongly diminished luminous efficacy. For this reason there is a strong interest in red-emitting narrow-band phosphors. One of the most promising phosphors in that respect is K₂SiF₆:Mn⁴⁺, with an emission spectrum that consists of five very narrow peaks in the 629-634 nm range, and a relative high quantum efficiency that can go up to 90% or more. The downside of this phosphor however is the relative slow decay of the excited states, causing optical quenching at higher input powers (starting at a few tens of W/cm^{2} [7].

Quantum dots (QDs) are often presented in the literature as another alternative for the conventional red nitride phosphors. A main advantage of QDs is their very short decay time [8], which offers high power saturation in the range of 10^4 W/cm² [9]. Other advantages of QDs are their narrow and size-dependent emission spectrum, potentially high, near unity quantum efficiency, and tiny particle size in the range of a few nanometers [10, 11]. Estrada et al. [6] stated that with traditional inorganic phosphors as down-conversion materials, the transition from R_a 80 to R_a 90 results in a lumen loss of 17% for a correlated color temperature of 2700 K. However, replacing red-emitting nitride phosphors with more narrow-band red-emitting quantum dots should reduce this efficiency drop to a mere 6% on a normalized lm/W basis. Such small differences are really advocating the adoption of CRI- R_a 90. To prove this point, Estrada et al. made use of Cd-based QDs with a PLQY in the range of 80-90% [6, 12, 13], a spectrally narrow emission with a full-width-at-half-maximum (FWHM) of 36 nm, and a minor overlap between the absorption and emission spectra. In 2019, Osram launched the first stable QD-based white LED on the market, which offers a 0.2 W output with an efficacy value of 173 lm/W at 3000 K and a R_a of 90. To the best of our knowledge, this LED also uses Cd-based QDs [14]. Cadmium, however, is a restricted element under the RoHS directive in the EU [13], and similar directives have been adopted by other regulators in, for example, Japan, South Korea [15], and California [16].

A promising cadmium-free alternative are InP-based QDs. The possibility to use such QDs as color convertors for white LEDs was already shown in the literature [17, 18]. While providing a proof-of-concept, the resulting QD-LEDs had low efficacy and did not reach the $R_a/R9$ color rendering standard. More in general, the implementation of alternatives to Cd-based QDs has often been questioned because of the wider emission spectrum and lower PLQY of such materials as compared to Cd-based quantum dots [13, 19, 20].

In this paper, we demonstrate that InP/ZnSe QDs with an emission line ~ 45 nm wide and a PLQY of $\sim 80\%$ are a viable alternative for making efficient, high-CRI white LEDs using on-chip color conversion. First, we evaluate the relation between the central emission wavelength and the linewidth on the maximal luminous efficacy and color rendering of a QD-LED by means of a theoretical emission spectrum. We find that the efficiency gain that comes with a narrower QD emission line is partially offset by the red-shift of that line needed to preserve color rendering. Importantly, this trade-off makes the need for narrow emission lines less stringent in the case of high-CRI white LEDs than for the LEDs that large-color gamut display applications need [21–23]. Building on these theoretical estimates, we fabricate white QD-LEDs with on-chip color convertors based on a mixture of red InP/ZnSe QDs with green powder phosphors. Focusing first on 4000 K spectra, we show that real QD-LEDs can indeed attain a color rendering performance in close agreement with current standards, i.e., $R_a \approx 90$, $R9 \approx 50$, by partially closing the cyan gap between the blue pump light and optimizing the central wavelength of red InP/ZnSe QDs. Next, we show that both for 3000 K and 4000 K spectra, QD-LEDs using red InP/ZnSe QDs attain a better luminous efficacy of radiation (LER) than LEDs using red nitride phosphors and are comparable to QD-LEDs using red Cd-based QDs. Finally, we argue that the main loss mechanism leading to a luminous efficacy of 132 lm/W at CCT = 4000 K for the best QD-LED is not the efficiency of the InP/ZnSe QDs, but rather the wall-plug efficiency of the blue LED and the light recycling in the LED package. We thus conclude that InP-based QDs are the most promising red emitter for efficient, high-CRI white LEDs based on on-chip color conversion.

2. Methods

2.1. Theoretical benchmark for color rendering and efficacy

The luminous efficacy (LE) is the ratio of the emitted luminous flux to the consumed electrical power. To investigate the maximal $R_a/R9$ and corresponding LE values that can be obtained by a phosphor-converted white LED that includes red-emitting QDs, we used a theoretical emission spectrum. This spectrum was constructed based on the following considerations. For any given CCT below 5000 K, maximal $R_a/R9$ values are obtained by the corresponding black body spectrum that is covering the full visible domain. However, to balance color rendering and LE, the emission spectrum of a practical phosphor-converted LED is typically cropped by the emission spectrum of the (blue) source LED at the short wavelength side and the emission spectrum of the red-emitting phosphor at the long-wavelength side. As we used a single blue source LED with a maximum emission intensity at 450 nm and FWHM of 20 nm for all our experimental results, we cropped the black body spectrum at short wavelengths with this spectrum. At the long wavelength side, on the other hand, we delimited the spectrum by a Gaussian line with an adjustable central wavelength λ_r and FWHM that represents the red emission of different QDs. Finally, we adjust the intensity of the blue LED and red QD band so as to keep the cropped black body spectrum at the desired CCT on the black body locus. Figure 1 shows an example of such a spectrum. The resulting spectrum provides a good trade-off between color rendering and LE, and serves as a benchmark for our experimental results.

The influence of the center wavelength (λ_r) and FWHM of the red QD emission band on the R_a, R9 and LE values was calculated using the Python LuxPy package [24]. For calculating the LE values, we assumed a lossless electrical to optical power conversion for the blue LED and we only considered Stokes losses for the QD color conversion. Hence, the resulting LE values correspond to theoretical maximum efficiencies for phosphor-converted white LEDs with red QDs as specified.

2.2. Experimental procedures

2.2.1. Synthesis of red-emitting InP/ZnSe core/shell QDs

Zinc(II)oleate synthesis We prepared zinc(II)oleate by the procedure proposed by Dhaene et al. [25,26]. In short, 3.66 g (45 mmol) of zinc(II)oxide was mixed with 20 mL (383 mmol) of acetonitrile. While cooling, 6.36 mL (45 mmol) trifluoroacetic anhydride and 0.69 mL (9 mmol) trifluoroacetic acid were added to this mixture. A clear and colourless solution



Fig. 1. Blackbody spectrum for CCT = 4000 K that is cropped by the blue-LED spectrum on the left side, and the red quantum dot spectrum (represented by a Gaussian distribution) on the right side.

was obtained upon reaching room temperature. This zinc trifluoroacetate solution was added to a mixture of 25.55 g (90.45 mmol) oleic acid, 10.29 g (101.7 mmol) triethylamine and 180 mL (2.351 mol) 2-propanol resulting in the formation of a white precipitate. Dissolution of the product occurred at reflux temperature and the subsequent slow cooling to -20 $^{\circ}$ C lead to white crystals that were filtered off and washed with cold methanol. The synthesized powder was dried under vacuum and a chemical yield of 94% is obtained.

· Colloidal synthesis of InP/ZnSe QDs

Raw materials, indium(III)chloride (50 mg (0.23 mmol)) and zinc(II)chloride (150 mg (1.10 mmol)), were mixed in 2.5 mL (7.58 mmol) of technical oleylamine. The mixture was stirred and degassed at 120 °C for an hour and then heated to 180 °C under inert atmosphere. Upon reaching 180 °C, a volume of 0.25 mL (0.91 mmol) tris(diethylamino)phosphine was quickly injected in the above mixture and the InP nanocrystal synthesis proceeded. After 30 minutes, the dispersion was cooled to 120 °. One gram (1.58 mmol) of zinc(II)stearate or zinc(II)oleate mixed in 1 mL (3.03 mmol) oleylamine and 2 mL (6.25 mmol) 1-octadecene were added. Subsequently, the mixture was stirred and degassed for an hour. Afterwards, 0.8 mL stoichiometric TOP-Se (2.24 M) mixture was injected and the temperature was raised to 330 °C. At this temperature, the shell growth went on for 28 minutes. Following on the reaction, the temperature was setted at 240 °C and 0.5 mL (2.09 mmol) dodecanethiol was swiftly injected when passing 300 °C. Ten minutes later, the reaction was stopped and the mixture was cooled down. InP/ZnSe QDs were then precipitated once in acetone, dispersed in toluene and stored in a N₂-filled glovebox. This procedure can be upscaled 5 times without changing the properties of the end product.

2.2.2. Preparation of white LEDs

We used LUXEON 3535 LED packages from Lumileds (see Figure 2), without the phosphor in polymer on top of the blue LED chip. These blue LED chips had an emission peak at 450 nm and a wall-plug efficiency of around 70% ($\pm 3.5\%$) when operated with a forward current of 50 mA at room temperature. To create a white LED with a specific CCT, this chip was coated with a color-convertor resin containing a mixture of traditional phosphors and red-emitting InP/ZnSe quantum dots. Inorganic phosphor powders (YAG:Ce (545 nm) and LuAG:Ce (516 nm)) were purchased from Intematix, while red InP/ZnSe QDs with FWHM = 45 ± 5 nm were synthesized by the protocol described above. The clear photopolymer resin from Formlabs [27] was used as binder material. This resin has a viscosity of 850 – 900 cps and a refractive index of 1.54

(@650 nm) after curing. Phosphor-containing resins were made by loading the required mass of the inorganic phosphors and the uncured resin in a vial, and adding a predetermined volume of a QD-in-toluene dispersion. After the toluene had evaporated, the mixture was homogenized, deposited in the LED recycling cavity with a micropipette, and cured. During this process, the high viscosity and short curing time – a few minutes – helped preventing phosphor sedimentation. Moreover, the photo-initiator in the resin enables the mixture to be cured using wavelengths at around 420 nm, which is helpful since light absorption by the quantum dots can completely prevent UV curing at shorter wavelengths. The spectral radiant flux of the resulting LEDs was measured with a custom-made integrating sphere [28]. LEDs were operated with a drive current of 50 mA and a typical forward voltage of 2.76 V, resulting in a corresponding electrical input power of 0.138 W.

2.3. Simulation model of white LED configuration

Reliable simulations are required to quantify the various loss mechanisms in an LED package and make predictions of potential performance improvements with a more efficient LED chip or quantum dots with higher quantum yield. Furthermore, simulations enable us to predict the composition of the color-convertor resin needed to obtain a specific emission spectrum, thereby avoiding time-consuming trial-and-error experiments.

To be accurate, the simulation model of a white LED package with multiple luminescent materials must include all interactions – absorption, emission, scattering, and re-absorption – of the blue source light and the photoluminescence light, with the different luminescent materials and the LED package. We implemented such simulations in LightTools [29], a commercially available ray-tracing software package.

The LED package and the simulation model, which includes the optical properties of the package and the blue LED chip, are shown in Figure 2. As can be seen, the package contained a single $580 \times 1143 \times 200 \ \mu$ m blue LED chip. The diameter and depth of the LED cup were 2.6 mm and 0.5 mm, respectively. We measured the specular reflectance of the bottom reflector and LED die, as well as the diffuse reflectance of the LED package side walls. The results can be seen in Figure 2c, and coincide more or less with the typical values stated in the literature [30, 31]. The blue LED chip was assumed to be a Lambertian emitting surface [32, 33]. When simulating this LED package filled with clear resin in optical contact with the blue chip, we found a reduction of the total outcoupled blue light from the LED package by 15-20%. Because this was in good agreement with the experimental results when filling the blue LED package with clear resin, we assume also for the encapsulated blue LED chip an EQE of 70%. Also when simulating the radiation pattern of the blue LED package filled with clear resin, we found a good match with the measured radiation pattern. This can be seen in Figure 3c.



Fig. 2. a - Image of the 'empty' LUXEON 3535 LED module, b - Simulation model of the LED package: 1-LED chip, 2-bottom reflector, 3-inner side of recycling cavity, 4-diffusing bar, 5-package. c - Reflectance of the LED package and blue chip.

2.4. Single-event optical properties of the luminescent color converters

The spectral luminous flux of a pc-LED package depends strongly on the scattering, absorption, emission and photoluminescence quantum yield (PLQY) of all luminescent materials included. These optical phenomena can be accurately modelled with the commercial ray-tracer LightTools, including multiple scattering and phosphor re-absorption [34]. The underlying model is a Monte-Carlo implementation of the fluorescent radiative transfer equation [35]. To solve correctly, this model needs the scattering coefficient (μ_s), the scattering phase function (P(v, v')), the absorption coefficient (μ_a), the emission spectrum and PLQY of all involved fluorescent materials. It is however very difficult to measure these properties directly, as measured quantities of luminescent materials are often the result from the repetitive absorption, scattering and emission of photons before they escape from the sample. Such multiple events can result in an ostensibly smaller photoluminescence quantum efficiency [36], red-shifted emission spectra [37], and inaccurate scattering parameters [38]. One way to mitigate these effects is to measure the optical properties of highly diluted samples. This approach, however, is often limited since measurements need a sufficient signal-to-noise ratio and light can be trapped by total internal reflection. Alternatively, reliable simulation parameters can be obtained by a reverse modelling approach.

For obtaining accurate single-event properties via reverse modelling, we prepared a series of thin phosphor films with fixed dimensions and different phosphor loadings. The absorbance of these films was measured in a Perkin Elmer spectrophotometer. Photoluminescence spectra were obtained by exiting the films in an integrating sphere [39] by a blue laser. Figure 3a shows an example for YAG:Ce phosphor. For the inorganic phosphor powders, the scattering properties were derived via Mie theory, for which the material density and particle size distribution were provided by the manufacturers. We neglected scattering by the quantum dots, since the scattering cross-section is much smaller than the absorption cross-section in this case [40].

We start from the listed (if available) material properties, and slightly adjust these properties in the simulation model of the phosphor films, until we obtain a good match of the measured and simulated spectral radiant flux (Figure 3a). A detailed discussion of the estimation accuracy of this method falls beyond the scope of this paper, but similar methodologies have also been described in the literature [41].



Fig. 3. a - Simulated and measured spectral power distribution of resin samples with different phosphor loadings: Sample 1 (1 ml resin + 0.32 g of YAG:Ce), Sample 2 (1 ml + 0.082 g YAG:Ce), Sample 3 (1 ml resin + 0.025 g YAG:Ce). b - Simulated/measured spectra of LED coated with 1 ml resin mixed with 0.048 g YAG:Ce. c - Simulated/measured radiation pattern of LED package filled with clear resin.

An overview of the relevant parameters and obtained spectra for all considered materials in this paper, are given in Table 1 and Figure 4 respectively. Wavelengths in parentheses after the material name represent the emission peak wavelength (PWL). Three different red QDs with PWL at 605, 611 and 618 nm were characterized. As shown, all of these QDs have FWHM = 45 ± 5 nm. Because single particle emission spectra of 15-25 nm wide were reported for red InP/SnSe QDs, this 45 nm linewidth is caused by heterogeneous broadening [42]. Since both absorption and scattering coefficient scale inversely with the used phosphor/QD loading in the LED package; the values for μ_a and μ_s are specified for the used loading's in QD-LED4 (see section 3.2). To make QD-LED4 we mixed 1 ml of UV curable resin with 0.093 g YAG:Ce, 0.19 g LuAG:Ce and 30 μ l of QDs (611 nm) from a 568 μ M QD solution.

Table 1. Scattering/absorption coefficient and PLQY of fluorescent materials

	InP/ZnS QDs	YAG:Ce (545 nm)	LuAG:Ce (516 nm)
$\mu_{\rm s}$ (@450 nm) [1/mm]	0	3.5	1.95
μ_{a} (@450 nm) [1/mm]	0.44	0.72	0.33
PLQY [%]	75 - 80	98	92



Fig. 4. Emission/absorption spectrum of YAG:Ce (545 nm), LuAG:Ce (516 nm) and red InP/ZnSe quantum dots.

3. Results and Discussion

3.1. A theoretical color rendering and efficacy of QD-LEDs

We used a theoretical emission spectrum (see Methods section) to investigate the maximal $R_a/R9$ and corresponding luminous efficacy values that can be obtained by a phosphor-converted white LED that includes red-emitting QDs. This theoretical emission spectrum is chosen to be representative of white LEDs with good color rendering performance ($R_a > 80$) and allowed us to identify trends in the relation between LE, color rendering and QD emission linewidth.

The influence of the center wavelength (λ_r) and FWHM of the red QD emission band on the R_a, R9 and LE values was calculated using the Python LuxPy package [24]. Figure 5 shows R_a, R9 and LE values of the theoretical emission spectrum (CCT = 4000 K) as a function of the peak wavelengths and FWHM of the red QD emission.



Fig. 5. The a) R_a , b) R9 and c) LE values of the cropped backbody spectrum (CCT = 4000 K) for different red peak wavelengths and FWHM. The purple isocurve connects the points where R_a has a value of 93, the R9 values on the curve are approximately 50, while LE changes but only slightly. As an example, the three points on the third graph indicate the exact values of LE for three different FWHM; one can notice that red QDs with more narrow FWHM must emit at longer wavelengths to achieve the same $R_a/R9$ values. As a result, differences in LE values are limited. Graph d) shows the dependence of LE on FWHM, for the case when R_a is 93.

As the center wavelength of the red emission shifts towards longer wavelengths and the emission line broadens, both R_a and R9 increase, while the LE decreases. Taking an FWHM of 45 nm, a realistic value for InP-based QDs, we find that R_a reaches 90 for a wavelength of 613 nm, while R9 would exceed 50 for a wavelength of 618 nm; the R_a at this wavelength is 93. Under these conditions, the LE amounts to 292 lm/W. Further shifts to longer wavelengths lead to additional increases of R_a and R9, yet this improved color rendering concurs with a strong reduction of the luminous efficacy. Considering a narrower emission line of 30 nm, which would be characteristic of CdSe-based QDs, a wavelength of 616 nm is needed to attain Ra values exceeding 90, but 621 nm is required to reach R9 of 50 ($R_a = 93$, LE = 297 lm/W). For the extreme case when FWHM = 15 nm ($R_a = 93$, R9 = 50), LE is only slightly higher and is 300 lm/W. Interestingly, the additional red-shift to attain good color rendering partially offsets the efficiency benefits imparted by a narrower emission line. To highlight the trade-off between color rendering and luminous efficacy that comes with a narrower emission line, Figure 5d represents the luminous efficacy as a function of the width of the emission line along the $R_a = 93$ isocurve that is represented as the purple line in Figure 5a-c. One indeed sees that the reduction of the LE with increasing FWHM is limited to a mere 0.33 lm/W per 1 nm increase of the FWHM. Hence, an increase in linewidth from 30 to 45 nm only results in an LE drop from 297 to 292 lm/W, i.e., a mere $\sim 2\%$ for the given choice of R_a. Since the R_a = 93 isocurve largely coincides with the R9=50 isocurve, we conclude that white QD-LEDs can achieve a theoretical luminous efficacy between 285 and 300 lm/W in combination with Ra 90 and R9 50 for emission lines centered at around 620 nm and having an FWHM below 50 nm.

When considering the above results, it is important to acknowledge that the actual values for R_a , LE and especially R9, will depend on the specific spectral shape of the white LED emission. Differences in the broadband green-yellow phosphor emission will result in different color rendering and luminous efficacy values. While analysing specific phosphors (combinations), we have found that the important trade-off between the FWHM of the red QD emission and resulting

LE for a specific color rendering performance is always similar (to a few %), provided that the resulting color point is the same. This motivates that the results in Fig. 4 are representative for the impact of the red QD emission FWHM on color rendering and luminous efficacy.

3.2. Experimental white light spectra of InP-based QD LEDs

For this study we used InP/ZnSe QDs with an emission linewidth of ~45 nm. According to the theoretical estimates represented in Figure 5, white QD-LEDs with R_a 90 and R9 50 can be obtained with such a linewidth, provided that the central emission line is around 620 nm. Importantly, this central emission of 620 nm refers to the QD emission as retrieved in the white light spectrum. This emission line can be redshifted from the (single-event) emission spectrum of the QDs because of their self-absorption [43]. Such effects will depend on the properties and the concentration of all used luminescent materials in the color-convertor resin, i.e., phosphors and QDs. To anticipate this red-shift, QD-LEDs were prepared using InP/ZnSe QDs with a single-event emission line centered at 605 nm.



Fig. 6. LED1 - Measured spectral power distribution of the white QD LED with $R_a = 80$. This white LED has a CCT ≈ 4100 K and a LE of 143 lm/W.

As a first reference QD-LED, we prepared color-convertor resins containing a YAG:Ce phosphor with peak wavelength at 545 nm (YAG:Ce 545) as a broadband phosphor and red InP/ZnSe quantum dots with a single-event peak emission at 605 nm and a PLQY of 75%. As can be seen in Figure 6, the resulting white light spectrum of QD-LED1 consists of a combination of the YAG:Ce and the QD emission; the latter giving an additional band centered at 610 nm. The white LED1 has a fairly high efficiency of 143 lm/W because most of the light is emitted near the maximum of the luminous efficiency function. The color rendering however is moderate with $R_a = 80$ and R9 = 2 for a CCT of 4100 K with chromaticity coordinates (x = 0.3776, y = 0.3837). Comparing the QD-LED1 spectrum with the theoretical spectrum shown in Figure 1 (see Methods section) and the theoretical color rendering estimates shown in Figure 5, we see two reasons for the moderate color rendering of the QD-LED1 spectrum. First, the spectrum features a significant cyan gap between the blue LED emission line and the YAG:Ce emission band, which is absent in the theoretical spectrum. Second, the effective position of the QD emission band at 610 nm is 10 nm to the blue of the preferred central wavelength between 615 and 620 nm.

To overcome these limitations we replaced YAG:Ce 545 by a LuAG:Ce phosphor with peak emission at 516 nm (QD LED2). As can be seen in Figure 7, the use of LuAG:Ce 516 significantly reduces the cyan gap in the QD-LED2 spectrum and limits the red emission tail coming from the YAG:Ce 545 emission in QD-LED1. This results in an $R_a = 91$, R9 = 23 and LE = 127 lm/W. In order to further improve the color rendering performance, the red QDs with peak emission at 605 nm were changed by red QDs with peak emission at 611 nm (QD LED3). With an $R_a = 94$ and



Fig. 7. LED2 - White QD LED with the cyan-region perfectly filled by using the LuAG:Ce phosphor, resulting in $R_a > 90$ (CCT ≈ 4200 K, x = 0.3755, y = 0.3888). LED3 - Measured spectral power distribution of the white LED using LuAG:Ce (516 nm) and red-emitting QDs (611 nm). It has both high $R_a = 94$ and R9 = 84 (CCT ≈ 4400 K, x = 0.3618, y = 0.3557).

R9 = 84, QD-LED3 offers excellent color rendering. This result, however, is attained at the cost of a lower luminous efficacy, which only reaches 113 lm/W.



Fig. 8. LED4 - Measured spectral power distribution of the white LED using LuAG:Ce (516 nm), YAG:Ce (545 nm) and red-emitting QDs (611 nm) as luminescent materials. This LED balances color rendering and LE performance.

As previously mentioned, R_a 90 and R9 50 are currently recommended standards for color rendering. From this perspective, QD-LED3 overdoes the trade-off between efficacy and color rendering. The reduction of the cyan gap clearly reduces efficacy. A better balance between efficacy and color rendering was found by means of a color-convertor resin based on an optimized mixture of LuAG:Ce 516, YAG:Ce 545, and InP/ZnSe QDs with a single-event peak emission at 611 nm and a PLQY of 78%. As shown in Figure 8, the resulting spectrum (QD-LED4) features a spectral radiant flux with a CCT \approx 4100 K (x = 0.3829, y = 0.3974), R_a = 88, R9 = 47 and luminous efficacy of 132 lm/W. A similar phosphor combination was used to fabricate 3000 K white LEDs (see Figure 9). Hence, in line with the theoretical estimates, we find that InP-based QD-LEDs can reach current color rendering standards, despite a relatively broad emission line of 45 nm.

3.3. Luminous efficacy of radiation

Since the white light QD-LED4 spectrum meets current color rendering standards, we used that spectrum as a starting point to compare the luminous efficacy of radiation (LER) for different white LEDs. The LER of a given spectrum is defined as the ratio of the luminous flux to the radiant flux, a ratio that depends on the position and the width of the QD emission band. The white LEDs that are considered in this comparison, all have similar color rendering properties (R_a 90 and R9 50), but use either InP/ZnSe QDs, Cd-based QDs, or a nitride phosphor as the red-emitting color convertor. Moreover, we evaluated spectra of white LEDs with a CCT of both 4000 and 3000 K. While the white LEDs based on InP/ZnSe QDs were prepared and measured in our lab, we used the spectral power distribution for the 3000 K LEDs with Cd-based QDs and nitride phosphors as published by Estrada et al. [6], and data on 4000 K LEDs were measured from two commercially available packages, i.e., the OSRAM Osconiq LED [44] with red-emitting Cd-based QDs and the Luxeon 3535 LED [45] package with a red-emitting nitride phosphor (this package was an updated/newer version of the used LED package for the InP/ZnS QD LEDs, with slightly different geometry).



Fig. 9. Spectra of different white LEDs with similar color rendering performance $(R_a = 90 / R9 \approx 50)$ for CCT = 3000 K and 4000 K. The white LEDs with red-emitting nitride-based phosphor induce clearly much more lumen loss compared to the QD-based LEDs due to the broad red tail that extends far beyond the human eye sensitivity curve.

LED type	LER (lm/W)	Compared to InP QDs
3000 K nitride phosp. [6]	274	-17%
3000 K Cd-based QDs [6]	340	+4.5%
3000 K InP/ZnSe QDs	325	
4000 K nitride phosp. [45]	285	-18.2%
4000 K Cd-based QDs [44]	314	-8.4%
4000 K InP/ZnSe QDs	345	

 Table 2. The luminous efficacy of radiation of white LEDs with different luminescent materials for the red emission

In Figure 9, we represented the different 3000 and 4000 K white LED spectra, normalized to the same total output power, while Table 2 summarizes the corresponding LERs. Considering the

3000 K LEDs first, one sees that the narrower red emission of the two white QD-LEDs, results in considerably larger LER as compared to the white LED with a nitride phosphor. More precisely, we find that the LER of the InP-based QD-LED spectrum is 17% larger than the nitride-based LED. Clearly, this is the result of the broad, red emission tail of the nitride phosphor, which extends well beyond the human eye sensitivity curve. On the other hand, the replacement of InP-based QDs by Cd-based QDs only results in a moderate increase of the LER by 4.5%. In line with our theoretical estimates, this limited impact of a more narrow emission line on the LER can also be linked to the slight red-shift of the emission line that is needed to preserve good color rendering. In the case of the 4000 K white LEDs, we similarly find that the LER of the nitride-based white LED is 18.2% smaller than that of the InP-based QD-LED. Opposite from our theoretical results, however, we find that the LER of the OSRAM Osconiq LED is smaller than of QD-LED4, even if the former LED uses Cd-based QDs. Looking at the spectrum of the OSRAM Osconiq LED, this is also the result of the relatively broad, red emission peak that is also present in this case. A possible reason for this, is the wider than expected emission line of the Cd-based QDs, but also the extension of the emission of the powder phosphor(s) in the far-red region is certainly possible. We thus conclude that while the replacement of broad emitting, nitride-based phosphors by QDs can significantly improve the LER of white LEDs; it is the overall phoshor-QD mixture that determines the final LER gains. In particular, the modest efficacy improvements expected for more narrow QD emission lines can easily be undone by the choice of the green-yellow phosphor in the color convertor.

3.4. Luminous efficacy of InP-based white LEDs



Fig. 10. a - Measured spectral power distribution of the demonstrated InP/ZnSe QD-LED3 (CCT=4000 K, LE=132 lm/W) and corresponding simulated spectrum. b - Pie chart of the various power losses in the demonstrated QD-LED4. The different loss mechanisms were estimated with the developed simulation model in LightTools.

While the LER of the QD-LED4 spectrum amounts to 345 lm/W, the actual QD-LED's luminous efficacy was 132 lm/W only, as indicated in section 3.2. For the Luxeon 3535 white LED with nitride phosphors (LER = 285 lm/W) we measured a luminous efficacy of 144 lm/W. For the OSRAM Osconiq LED with Cd-based QDs (LER = 314 lm/W) we measured a luminous efficacy of 170 lm/W. So despite the larger LER of the InP/ZnSe QD-LED, the measured luminous efficacy of this LED is significantly smaller than the measured luminous efficacy of the other considered white LEDs at CCT = 4000 K.

To get more detailed insight into the QD-LED energy power budget, the different loss mechanisms and the resulting efficacy, we simulated the output spectrum of QD-LED4 using the geometry of the LED package and the properties of the different convertor materials as input (see Methods section). Figure 10a represents the experimental and simulated spectral radial flux, where the excellent match between both provides a solid basis to quantify the losses. Considering

the measured wall plug efficiency of 70% for the blue LED, the simulated output spectrum yields a total power budget for QD-LED4, as depicted in Figure 10b. According to this diagram, we attribute the optical losses – expressed as a fraction of the total power budget – of QD-LED4 to:

- (13.5%) Stokes losses in the luminescent materials.
- (11.5%) Absorption losses within the LED package, for example related to non-perfect reflective interfaces.
- (6%) Non-radiative losses due to a non-unity photoluminescence quantum yield of the luminescent materials.
- (1%) Absorption losses in the polymer binder.

As a result, 38% of the electric power is retrieved as optical power yielding a luminous efficacy of 132 lm/W.



Fig. 11. Predicted luminous efficacy values of the InP/ZnS QD LED with CCT = 4000 K for a- varying wall-plug efficiency of the blue LED chip and b- varying quantum yield of the InP/ZnSe quantum dots.

While Stokes losses or reflection losses are difficult, if not impossible to avoid, a further enhancement of the luminous efficacy can result from an increased wall-plug efficiency of the blue LED and a higher PLQY of the luminescent materials. Using our simulation model for OD-LED4, we evaluated both aspects of the power budget separately. In Figure 11a, the variation of the luminous efficacy with the blue chip efficiency is shown, when the PLQY of the red QDs equals 80%. As can be expected, the QD LED efficacy increases linearly with the wall-plug efficiency to reach a maximum of 188.5 lm/W for a 100% efficient electrical to optical power conversion. While this figure remains well below the LER of 345 lm/W, this result also shows that a considerable gain of around 2 lm/W can be made for every percentage increase of the wall-plug efficiency of the blue LED. As compared to such gains, the impact of a further rise of the PLQY of the InP/ZnSe QDs is more limited. In Figure 11b, the variation of the luminous efficacy with the PLQY of the red QDs is shown, when the blue chip efficiency equals 70%. The relation between the luminous efficacy of the QD-LED and the PLQY of the red QDs is clearly non-linear where the gains of increasing the PLQY drop for the highest PLQYs. This non-linear relation is a direct consequence of the multiple re-absorption effects that occur in the white QD LED. If the PLQY of the red QDs is lower, a higher QD concentration is needed to reach the same color point. This higher OD concentration not only results in more absorption of blue light, but also more absorption of the green-yellow light emitted by the YAG:Ce and LuAg:Ce phosphors and also more self-absorption of red light emitted by the QDs themselves. The negative impact of these multiple re-absorption effects on the luminous efficacy increases

considerably when the PLQY of the QDs is lower. As a result, replacing 80% efficient by 100% efficient QDs only increases the LE from 132 to 141 lm/W, whereas using 40% efficient QDs would reduce the LE to 104 lm/W. In order to evaluate the combined impact of both the blue chip and red QD efficiency on the luminous efficacy, one can simply multiply the linear increase as a consequence of the blue chip efficiency increase, with the non-linear increase as a consequence of the red QD PLQY increase. This would result for example in a LE = $(0.7)^{-1} \times 141 = 201$ lm/W for a perfect efficiency of both the blue LED and red QDs.

Despite the larger LER of the InP/ZnSe QD-LED, the measured luminous efficacy was lower than that of the other two considered white LEDs at CCT = 4000 K. The power budget estimates made in the above paragraphs indicate that this difference is not mainly caused by the use of poor red-emitting QDs, but rather the lower wall-plug efficiency of the blue LED chip or the lower light recycling ability of the used package. Taking these considerations into account, we conclude that a combination of traditional inorganic phosphors and InP/ZnSe QDs can lead to white QD-LEDs that combine high efficiency with excellent color rendering, a result that is not hampered by emission lines being 45 nm wide.

4. Conclusion

In this study, we show that InP/ZnSe quantum dots with a FWHM bandwidth = 45 nm and a quantum efficiency of nearly 80% offer a competitive alternative to already well-developed and commercially available Cd-based QDs. Both our theoretical calculations and experimental results show that the efficiency penalty for the wider emission spectrum compared to narrow-band Cd-based QDs remains under 5% in all cases. The best result using a Lumileds 3535 package with a blue-chip wall-plug efficiency of 70% is an overall luminous efficacy of 132 lm/W for $R_a \approx 90$, $R9 \approx 50$, at CCT ≈ 4000 K. Using the developed simulation model, we showed that this result corresponds with 94% of the maximal possible luminous efficacy with this package in case that QD materials would have had a unity quantum yield.

In this paper, we considered the optical properties and application of InP/ZnSe QDs for white LEDs with good color rendering and high efficacy. In future work, we will address the reliability of the InP/ZnS QDs under high flux-densities and elevated temperature, as well as the process ability of these QDs.

Funding.

This work was financially supported by the SBO-project QDOCCO within the SIM SoPPoM+ program of the Flemish Strategic Initiative for Materials (SIM) and Ghent University (GOA no. 01G01019).

Acknowledgments.

We are grateful to Lumileds for providing us with a large batch of empty 3535 LED packages and relevant information about this specific package. Special thanks also go to Prof. Philippe Smet and Prof. Kevin Smet for some useful suggestions and guidelines.

Disclosures.

The authors declare no conflicts of interest.

Data Availability Statement.

Data underlying the results presented in this paper are not publicly available at this time but may be obtained from the authors upon request.

References

- 1. P. Morgan Pattison, M. Hansen, and J. Y. Tsao, "LED lighting efficacy: Status and directions," Comptes Rendus Physique **19**, 134–145 (2018).
- C. I. de l'Eclairage, "Measuring and specifying colour rendering properties of light sources," CIE Publication 13.3, CIE: Vienna, 1995.
- K. Houser, M. Mossman, K. Smet, and L. Whitehead, "Tutorial: Color Rendering and Its Applications in Lighting," LEUKOS - J. Illum. Eng. Soc. North Am. 12, 7–26 (2016).

- 4. M. Wright, "California tightens color performance of LEDbased lamps," LEDs Mag. (2016).
- M. Wei, K. W. Houser, A. David, and M. R. Krames, "Perceptual responses to LED illumination with colour rendering indices of 85 and 97," Light. Res. Technol. 47, 810–827 (2015).
- D. Estrada, K. Shimizu, M. Bohmer, S. Gangwal, T. Diederich, S. Grabowski, G. Tashjian, D. Chamberlin, O. B. Shchekin, and J. Bhardwaj, "32-1: On-chip Red Quantum Dots in White LEDs for General Illumination," SID Symp. Dig. Tech. Pap. 49, 405–408 (2018).
- 7. H. F. Sijbom, R. Verstraete, J. J. Joos, D. Poelman, and P. F. Smet, "K2sif6:mn4+ as a red phosphor for displays and warm-white leds: a review of properties and perspectives," Opt. Mater. Express 7, 3332–3365 (2017).
- X. Fan, T. Wu, B. Liu, R. Zhang, H. C. Kuo, and Z. Chen, "Recent developments of quantum dot based micro-led based on non-radiative energy transfer mechanism," Opto-Electronic Adv. 4, 1–15 (2021).
- 9. A. Tierno, T. Ackemann, C. G. Leburn, and C. T. Brown, "Saturation of absorption and gain in a quantum dot diode with continuous-wave driving," Appl. Phys. Lett. 97, 23–25 (2010).
- 10. A. P. Alivisatos, "Semiconductor clusters, nanocrystals, and quantum dots," Science 271, 933–937 (1996).
- S. Abe, J. J. Joos, L. I. Martin, Z. Hens, and P. F. Smet, "Hybrid remote quantum dot/powder phosphor designs for display backlights," Light. Sci. Appl. 6, 1–9 (2017).
- J. Kurtin, B. Mangum, and B. Theobald, "On-chip quantum dots for high color gamut displays," Dig. Tech. Pap. -SID Int. Symp. 48, 447–450 (2017).
- B. D. Mangum, T. S. Landes, B. R. Theobald, and J. N. Kurtin, "Exploring the bounds of narrow-band quantum dot downconverted LEDs," Photonics Res. 5, A13 (2017).
- 14. Osram Opto Semiconductors, "Quantum dots from osram make leds even more efficient," [retrieved 26 Juni 2020], https://www.osram.com/os/press/press-releases/ quantum-dots-from-osram-make-leds-even-more-efficient-osconiq-s-3030-qd. jsp.
- R. Guide, "Rohs initiatives worldwide," [retrieved 9 January 2021], https://www.rohsguide.com/ rohs-future.htm.
- 16. NIST, "Compliance faqs: Rohs," [retrieved 26 Juni 2020], https://www.nist.gov/standardsgov/ compliance-faqs-rohs.
- J. Ziegler, S. Xu, E. Kucur, F. Meister, M. Batentschuk, F. Gindele, and T. Nann, "Silica-coated InP/ZnS nanocrystals as converter material in white LEDs," Adv. Mater. 20, 4068–4073 (2008).
- S. Kim, T. Kim, M. Kang, S. K. Kwak, T. W. Yoo, L. S. Park, I. Yang, S. Hwang, J. E. Lee, S. K. Kim, and S. W. Kim, "Highly luminescent InP/GaP/ZnS nanocrystals and their application to white light-emitting diodes," J. Am. Chem. Soc. 134, 3804–3809 (2012).
- K. T. Shimizu, M. Böhmer, D. Estrada, S. Gangwal, S. Grabowski, H. Bechtel, E. Kang, K. J. Vampola, D. Chamberlin, O. B. Shchekin, and J. Bhardwaj, "Toward commercial realization of quantum dot based white light-emitting diodes for general illumination," Photonics Res. 5, A1 (2017).
- Q. A. Akkerman, G. Rainò, M. V. Kovalenko, and L. Manna, "Genesis, challenges and opportunities for colloidal lead halide perovskite nanocrystals," Nat. materials 17 (2018).
- H. Chen, J. He, and S.-t. Wu, "Recent Advances on Quantum-Dot-Enhanced Liquid-Crystal Displays," IEEE J. Sel. Top. Quantum Electron. 23 (2017).
- G. Harbers and C. Hoelen, "LP-2: High Performance LCD Backlighting using High Intensity Red, Green and Blue Light Emitting Diodes," SID Symp. Dig. Tech. Pap. 32, 702 (2001).
- 23. Z. Liu, C. H. Lin, B. R. Hyun, C. W. Sher, Z. Lv, B. Luo, F. Jiang, T. Wu, C. H. Ho, H. C. Kuo, and J. H. He, "Micro-light-emitting diodes with quantum dots in display technology," Light. Sci. Appl. 9, 1–24 (2020).
- K. A. Smet, "Tutorial: The LuxPy Python Toolbox for Lighting and Color Science," LEUKOS J. Illum. Eng. Soc. North Am. 16, 179–201 (2020).
- E. Dhaene, J. Billet, E. Bennett, I. Van Driessche, and J. De Roo, "The Trouble with ODE: Polymerization during Nanocrystal Synthesis," Nano Lett. 19, 7411–7417 (2019).
- M. P. Hendricks, M. P. Campos, G. T. Cleveland, J. L. P. Ilan, and J. S. Owen, "A tunable library of substituted thiourea precursors to metal sulfide nanocrystals," Science pp. 1226—1230 (2015).
- 27. Clear Resin, "Formlabs Inc.," Somerville, Massachusetts, United States.
- P. Hanselaer, A. Keppens, S. Forment, W. R. Ryckaert, and G. Deconinck, "A new integrating sphere design for spectral radiant flux determination of light-emitting diodes," Meas. Sci. Technol. 20 (2009).
- 29. LightTools 8.7.0, "Synopsys Optical Solutions," Mountain view, Colifornia, United States.
- 30. K. Wang, S. Liu, X. Luo, and D. Wu, Freeform Optics for LED Packages and Applications (Wiley, 2017).
- 31. J. K. Kim, H. Luo, E. F. Schubert, J. Cho, C. Sone, and Y. Park, "Strongly enhanced phosphor efficiency in GaInN white light-emitting diodes using remote phosphor configuration and diffuse reflector cup," Jpn. J. Appl. Physics, Part 2: Lett. 44 (2005).
- C.-C. Sun, T.-X. Lee, S.-H. Ma, Y.-L. Lee, and S.-M. Huang, "Precise optical modeling for LED lighting verified by cross correlation in the midfield region," Opt. Lett. 31, 2193 (2006).
- 33. I. Moreno and C.-C. Sun, "Modeling the radiation pattern of LEDs," Opt. Express 16, 1808 (2008).
- 34. M. W. Zollers, H. Yang, J. H. Melman, S. R. David, G. Wang, and X. Xu, "Process to measure particulate downconverting phosphors and create well-correlated software models of LED performance," Light. Diodes: Materials, Devices, Appl. for Solid State Light. XV 7954, 795414 (2011).

- 35. Y. Ma, M. Wang, J. Sun, R. Hu, and X. Luo, "Phosphor modeling based on fluorescent radiative transfer equation," Opt. Express 26, 16442–16455 (2018).
- 36. J. Ryckaert, A. Correia, M. D. Tessier, D. Dupont, Z. Hens, P. Hanselaer, and Y. Meuret, "Selecting the optimal synthesis parameters of inp/cdxzn 1-x se quantum dots for a hybrid remote phosphor white led for general lighting applications," Opt. Express 25, A1009 (2017).
- 37. W. Zhang, D. Dai, X. Chen, X. Guo, and J. Fan, "Red shift in the photoluminescence of colloidal carbon quantum dots induced by photon reabsorption," Appl. Phys. Lett. **104** (2014).
- S. Leyre, Y. Meuret, G. Durinck, J. Hofkens, G. Deconinck, and P. Hanselaer, "Estimation of the effective phase function of bulk diffusing materials with the inverse adding-doubling method," Appl. Opt. 53, 2117–2125 (2014).
- S. Leyre, E. Coutino-Gonzalez, J. J. Joos, J. Ryckaert, Y. Meuret, D. Poelman, P. F. Smet, G. Durinck, J. Hofkens, G. Deconinck, and P. Hanselaer, "Absolute determination of photoluminescence quantum efficiency using an integrating sphere setup," Rev. Sci. Instruments 85 (2014).
- 40. J. Li, Y. Tang, Z. Li, X. Ding, D. Yuan, and B. Yu, "Study on scattering and absorption properties of quantum-dotconverted elements for light-emitting diodes using finite-difference time-domain method," Materials 10 (2017).
- Z. Liu, S. Liu, K. Wang, and X. Luo, "Measurement and numerical studies of optical properties of yag:ce phosphor for white light-emitting diode packaging," Appl. Opt. 49, 247–257 (2010).
- I. Moreels, J. C. Martins, and Z. Hens, "Solution NMR techniques for investigating colloidal nanocrystal ligands: A case study on trioctylphosphine oxide at InP quantum dots," Sensors Actuators, B: Chem. 126, 283–288 (2007).
- J. S. Li, Y. Tang, Z. T. Li, K. Cao, C. M. Yan, and X. R. Ding, "Full spectral optical modeling of quantum-dot-converted elements for light-emitting diodes considering reabsorption and reemission effect," Nanotechnology 29, 295707 (2018).
- 44. OSRAM Opto Semiconductors, "OSCONIQ® S 3030, GW QSLM31.QM," [retrieved 8 December 2020], https://www.osram.com/ecat/OSCONIQ%C2%AE%20S%203030%20GW%20QSLM31.QM/com/en/class_pim_web_catalog_103489/prd_pim_device_8390008.
- 45. Lumileds, "Luxeon 35351 line," [retrieved 26 Juni 2020], https://www.lumileds.com/products/ mid-power-leds/luxeon-35351/.